NORYL™ PPE POWDERS + CONCENTRATES 6390H

REGION EUROPE

DESCRIPTION

NORYL 6390H resin concentrate is an non-reinforced blend of polyphenylene ether (PPE) + high impact polystyrene (HIPS). This material is in granule form and is optimized for blending with polystyrene resins. NORYL 6390H resin may be an excellent candidate in microwavable food packaging applications. This product is not certified per food contact regulations in US + EUR. Certification would be dependent on end-part testing.

GENERAL INFORMATION	
Features	Hydrolytic Stability, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Transparent/Translucent, Creep resistant, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Circuit Boards/Additives
Packaging	Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20260330

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yield, 50 mm/min	81	MPa	ISO 527
Tensile Stress, break, 50 mm/min	77	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	7	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	115	MPa	ISO 178
Flexural Modulus, 2 mm/min	2600	MPa	ISO 178
IMPACT [1]			
Izod Impact, notched 80*10*4 +23°C	5	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m²	ISO 180/1A
THERMAL [1]			
Vicat Softening Temp, Rate B/120	191	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	165	°C	ISO 75/Af
PHYSICAL [1]			
Density	1.07	g/cm³	ISO 1183
Matrix Tg	198	°C	DMA
Melt Volume Rate			
280°C/10.0 kg	4	cm³/10 min	ISO 1133
280°C/21.6 kg	10	cm³/10 min	ISO 1133

© 2026 Copyright by SABIC. All rights reserved

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved