

# NORYL™ RESIN GFN1

REGION EUROPE

## DESCRIPTION

NORYL GFN1 resin is a 10% glass fiber reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This general-purpose injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability. NORYL GFN1 carries a UL746C outdoor suitability rating of F1 and is an excellent candidate for a variety of indoor and outdoor applications including construction, electrical components + displays, lawn and garden equipment. \*See NORYL GFN1F resin for FDA food compliant / NSF version.

GENERAL INFORMATION	
Features	Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Taber Abrasion, CS-17, 1 kg	50	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	50	MPa	ISO 527
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	4	%	ISO 527
Tensile Modulus, 1 mm/min	4000	MPa	ISO 527
Flexural Stress, break, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	3500	MPa	ISO 178
Ball Indentation Hardness, H358/30	100	MPa	ISO 2039-1
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched 80*10*4 +23°C	20	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	20	kJ/m <sup>2</sup>	ISO 180/1U
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	25	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	25	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL <sup>(1)</sup></b>			
Thermal Conductivity	0.24	W/m·°C	ISO 8302
CTE, 23°C to 80°C, flow	5.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.E-05	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	135	°C	ISO 306
Vicat Softening Temp, Rate B/50	125	°C	ISO 306
Vicat Softening Temp, Rate B/120	130	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	130	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	115	°C	ISO 75/Ae
<b>PHYSICAL <sup>(1)</sup></b>			
Mold Shrinkage on Tensile Bar, flow <sup>(2)</sup>	0.3 – 0.5	%	SABIC method
Density	1.17	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.2	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	8	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity	1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.8	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0005	-	IEC 60250
Dissipation Factor, 1 MHz	0.001	-	IEC 60250
Relative Permittivity, 50/60 Hz	2.8	-	IEC 60250
Hot-Wire Ignition (HWI), PLC 0	≥3	mm	UL 746A
<b>FLAME CHARACTERISTICS <sup>(3)</sup></b>			
UL Yellow Card Link	<a href="#">E45329-236754</a>	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
Glow Wire Flammability Index 750°C, passes at <sup>(4)</sup>	3.2	mm	IEC 60695-2-12
Oxygen Index (LOI)	26	%	ISO 4589
<b>INJECTION MOLDING <sup>(5)</sup></b>			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 3	Hrs	
Melt Temperature	280 – 300	°C	
Nozzle Temperature	260 – 280	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 120	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.

(4) Value shown here is based on internal measurement.

(5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.



## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.