

LNPT[™] ELCRIN[™] EXL1414TB

DESCRIPTION

ELCRIN EXL1414TB polycarbonate (PC) siloxane copolymer is transparent injection molding grade with major component synthesized from Bio source. This resin offers extreme low temperature (-40 degrees) ductility in combination with medium flow characteristics and excellent processability with opportunities for shorter IM cycle times compared with standard PC. ELCRIN EXL1414TB resin is a general purpose product available in transparent and opaque colors and is an excellent candidate for a broad range of applications.

GENERAL INFORMATION	
Features	Chemical Resistance, Good Processability, Amorphous, Bio-Renewable, Aesthetics/Visual effects, Transparent/Translucent, High temperature resistance, Impact resistant, Low temperature impact, No PFAS intentionally added
Brands	LNPT [™] ELCRIN [™]
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Recreational /Specialty Vehicles
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	59	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5.6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	124	%	ASTM D638
Tensile Modulus, 50 mm/min	2180	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	90	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2180	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	56	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.4	%	ISO 527
Tensile Strain, break, 50 mm/min	108	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Strength, 2 mm/min	88	MPa	ISO 178
Flexural Modulus, 2 mm/min	2120	MPa	ISO 178
Hardness, Rockwell L	87	-	ISO 2039-2
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	820	J/m	ASTM D256
Izod Impact, notched, -30°C	710	J/m	ASTM D256
Izod Impact, notched 80*10*3 +23°C	65	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	55	kJ/m ²	ISO 180/1A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	70	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	60	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Instrumented Dart Impact Total Energy, 23°C	75	J	ASTM D3763
Instrumented Dart Impact Total Energy, -30°C	77	J	ASTM D3763
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D648
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	116	°C	ISO 75/Ae
CTE, -40°C to 40°C, flow	6.7E-5	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8E-5	1/°C	ASTM E831
CTE, 23°C to 80°C, flow	6.7E-5	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8E-5	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	138	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	139	°C	ISO 306
Ball Pressure Test, 125°C +/- 2°C	Pass	-	IEC 60695-10-2
PHYSICAL ⁽¹⁾			
Specific Gravity	1.19	-	ASTM D792
Density	1.19	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62
Water Absorption, (23°C/saturated)	0.12	%	ISO 62-1
Melt Flow Rate, 300°C/ 1.2 kgf	10	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/ 1.2 kg	9	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽²⁾	0.4 – 0.8	%	SABIC method
ELECTRICAL ⁽³⁾			
Hot-Wire Ignition (HWI), PLC 2	≥3.0	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 1	≥1.5	mm	UL 746A
FLAME CHARACTERISTICS ⁽³⁾			
UL Yellow Card Link	<u>E207780-314453</u>	-	-
UL Recognized, 94HB Flame Class Rating	≥0.4	mm	UL 94
UL Recognized, 94V-2 Flame Class Rating	≥3.0	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	70 – 95	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.