

LNPTM STAT-KONTM COMPOUND OX92182

PDX-O-92182

DESCRIPTION

LNP STAT-KON OX92182 compound is based on Polyphenylene Sulfide (PPS) branched resin containing glass fiber, carbon fiber and mineral. Added features of this grade include: Electrically Conductive Dimensional Stability.

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, Dimensional stability, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber, Glass Fiber, Mineral
Polymer Types	Polyphenylene Sulfide, Branched (PPS, Branched)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	145	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.3	%	ISO 527
Tensile Modulus, 1 mm/min	17500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	200	MPa	ISO 178
Flexural Modulus, 2 mm/min	16500	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	1.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	4.6E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	250	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.1	%	ISO 294
Density	1.62	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.05	%	ISO 62-1
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽³⁾	1.E+03 – 1.E+06	Ω	ASTM D257
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	315 – 320	°C	
Front - Zone 3 Temperature	330 – 345	°C	
Middle - Zone 2 Temperature	320 – 330	°C	
Rear - Zone 1 Temperature	305 – 315	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Measurement meets requirements as specified in ASTM D4496.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.