

LNPTTM THERMOCOMPTM COMPOUND DX1 1355

DESCRIPTION

LNP THERMOCOMP DX1 1355 compound is based on Polycarbonate (PC) resin containing proprietary fillers and available in black color only. Added features of this grade include: Improved Plating Surface and Mechanical Performance targeted for Laser Direct Structuring (LDS) applications, Improved Impact, Non-Brominated, Non-Chlorinated Flame Retardant.

GENERAL INFORMATION	
Features	Flame Retardant, Dielectrics, Laser Direct Structuring, Non Cl/Br flame retardant, Impact resistant
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Interiors
Consumer	Personal Accessory
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	52	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5.4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	70	%	ASTM D638
Tensile Modulus, 50 mm/min	2600	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	90	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	89	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	800	J/m	ASTM D256
Izod Impact, notched, -30°C	167	J/m	ASTM D256
Izod Impact, unnotched, -30°C	2120	J/m	ASTM D4812
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	114	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.2E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.7E-05	1/°C	ASTM E831
Relative Temp Index, Elec ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	80	°C	UL 746B
PHYSICAL ⁽¹⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Density	1.27	g/cm ³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.01	%	ASTM D570
Mold Shrinkage, flow, 24 hrs ⁽³⁾	0.5	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs ⁽³⁾	0.5	%	ASTM D955
Melt Flow Rate, 300°C/1.2 kgf	12	g/10 min	ASTM D1238
ELECTRICAL⁽¹⁾			
Relative Permittivity, 1 GHz	2.92	-	IEC 60250
Dissipation Factor, 1 GHz	0.007	-	IEC 60250
FLAME CHARACTERISTICS⁽²⁾			
UL Yellow Card Link	E207780-101214685	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.6	mm	UL 94
INJECTION MOLDING⁽⁴⁾			
Drying Temperature	100 – 110	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	275 – 300	°C	
Nozzle Temperature	275 – 300	°C	
Front - Zone 3 Temperature	260 – 300	°C	
Middle - Zone 2 Temperature	255 – 295	°C	
Rear - Zone 1 Temperature	250 – 290	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.