

LNPTM THERMOCOMPTM COMPOUND 2C003

FP-EC-1003

DESCRIPTION

LNP THERMOCOMP 2C003 compound is based on Ethylene Tetrafluoroethylene (ETFE) resin containing 15% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength
Fillers	Carbon Fiber
Polymer Types	Ethylene Tetrafluoroethylene Copolymer (ETFE)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Energy Management, Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	90	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	90	MPa	ASTM D638
Tensile Strain, break	4.9	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	4.9	%	ASTM D638
Tensile Modulus, 50 mm/min	11710	MPa	ASTM D638
Flexural Stress	137	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	137	MPa	ASTM D790
Flexural Modulus	11030	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	11030	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	1238	J/m	ASTM D4812
Izod Impact, notched, 23°C	352	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	207	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.73	g/cm ³	ASTM D792
INJECTION MOLDING ⁽²⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Melt Temperature	315	°C	
Front - Zone 3 Temperature	325 – 340	°C	
Middle - Zone 2 Temperature	300 – 325	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	280 – 300	°C	
Mold Temperature	90 – 120	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.