

# LNPTM THERMOCOMPTM COMPOUND RB008

RB-1008

REGION ASIA

## DESCRIPTION

LNP THERMOCOMP RB008 compound is based on Nylon 6/6 resin containing 40% glass bead.

GENERAL INFORMATION	
Features	Low Warpage, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Bead
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Consumer	Home Appliances
Hygiene and Healthcare	Pharmaceutical Packaging and Drug Delivery

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, break	55	MPa	ASTM D638
Tensile Strain, break	3.3	%	ASTM D638
Tensile Modulus, 50 mm/min	5100	MPa	ASTM D638
Flexural Stress	102	MPa	ASTM D790
Flexural modulus	3780	MPa	ASTM D790
Tensile Stress, break	58	MPa	ISO 527
Tensile Strain, break	2.7	%	ISO 527
Tensile Modulus, 1 mm/min	5300	MPa	ISO 527
Flexural Stress	103	MPa	ISO 178
Flexural Modulus	4060	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C	229	J/m	ASTM D4812
Izod Impact, notched, 23°C	32	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	4	J	ASTM D3763
Multiaxial Impact	4	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	20	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	2	kJ/m²	ISO 180/1A
<b>THERMAL <sup>(1)</sup></b>			
HDT, 1.82 MPa, 3.2mm, unannealed	68	°C	ASTM D648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	102	°C	ISO 75/Af
Relative Temp Index, Elec <sup>(2)</sup>	65	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Temp Index, Mech w/impact <sup>(2)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	65	°C	UL 746B
PHYSICAL <sup>(1)</sup>			
Density	1.46	g/cm <sup>3</sup>	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	1.2	%	ASTM D570
Mold Shrinkage, flow, 24 hrs <sup>(3)</sup>	1.8 – 2	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs <sup>(3)</sup>	1.9 – 2.1	%	ASTM D955
Mold Shrinkage, flow, 24 hrs <sup>(3)</sup>	1.8 – 2	%	ISO 294
Mold Shrinkage, xflow, 24 hrs <sup>(3)</sup>	1.9 – 2.1	%	ISO 294
Density	1.45	g/cm <sup>3</sup>	ISO 1183
Moisture Absorption (23°C / 50% RH)	1.55	%	ISO 62
FLAME CHARACTERISTICS <sup>(2)</sup>			
UL Yellow Card Link	<a href="#">E207780-101345249</a>	-	-
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING <sup>(4)</sup>			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.