

LNPTM STAT-KONTM COMPOUND AE001

REGION EUROPE

DESCRIPTION

LNP STAT-KON AE001 compound is based on Acrylonitrile Butadiene Styrene (ABS) resin containing 7% carbon fiber. Added features of this grade include: Electrically Conductive

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Acrylonitrile Butadiene Styrene (ABS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Hydrocarbon and Energy	Energy Storage
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20240703

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Modulus, 1 mm/min	5850	MPa	ISO 527
Tensile Stress, break, 5 mm/min	63	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.5	%	ISO 527
Flexural Modulus, 2 mm/min	5400	MPa	ISO 178
Flexural Strength, 2 mm/min	88	MPa	ISO 178
Flexural Modulus, 1.3 mm/min, 50 mm span	5630	MPa	ASTM D790
Flexural Strength, 1.3 mm/min, 50 mm span	89	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	15	kJ/m ²	ISO 179/1eU
Izod Impact, notched, 23°C	60	J/m	ASTM D256
Izod Impact, unnotched, 23°C	198	J/m	ASTM D4812
THERMAL ⁽¹⁾			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	101	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	107	°C	ISO 75/Bf
Vicat Softening Temp, Rate B/50	104	°C	ISO 306
Vicat Softening Temp, Rate B/120	105	°C	ISO 306
CTE, -40°C to 40°C, flow	3.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	1.06E-04	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	98	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	106	°C	ASTM D648
Vicat Softening Temp, Rate B/50	104	°C	ASTM D1525
Vicat Softening Temp, Rate B/120	105	°C	ASTM D1525
CTE, -40°C to 40°C, flow	3.3E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	1.06E-04	1/°C	ASTM E831
PHYSICAL ⁽¹⁾			
Density	1.07	g/cm ³	ISO 1183
Moisture Absorption, (23°C/50% RH/24hrs)	0.03	%	ISO 62-4
Moisture Absorption, (23°C/50% RH/Equilibrium)	0.12	%	ISO 62-4
Water Absorption, (23°C/24hrs)	0.35	%	ISO 62-1
Water Absorption, (23°C/saturated)	0.85	%	ISO 62-1
Melt Volume Rate, MVR at 230°C/10.0 kg	13.5	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow ⁽²⁾	0.2 – 0.4	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.2 – 0.4	%	SABIC method
ELECTRICAL ⁽¹⁾			
Surface Resistivity	1.E+03 – 1.E+06	Ω	ASTM D4496
Volume Resistivity	1.E+02 – 1.E+04	Ω.cm	ASTM D4496
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Drying Time (Cumulative)	12	Hrs	
Maximum Moisture Content	0.05 – 0.1	%	
Hopper Temperature	40	°C	
Melt Temperature	255 – 270	°C	
Rear - Zone 1 Temperature	220 – 240	°C	
Middle - Zone 2 Temperature	230 – 250	°C	
Front - Zone 3 Temperature	240 – 270	°C	
Nozzle Temperature	240 – 270	°C	
Mold Temperature	70 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw speed (Circumferential speed)	0.15 – 0.25	m/s	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.