LNP™ THERMOCOMP™ Compound D151RCC

DESCRIPTION

LNP THERMOCOMP D151RCC compound is based on recycled Polycarbonate (PC) resin containing 10% glass fiber. Added features of this grade include: High Modulus, Good Surface, Low Warpage, Good Ductility, Non-Brominated & Non-Chlorinated Flame Retardant. Post-Consumer Recycling (PCR) Polycarbonate content up to 50%.

GENERAL INFORMATION	
Features	Flame Retardant, Mechanical Recycling, Dimensional stability, High stiffness/Strength
Fillers	Glass Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Home Appliances, Commercial Appliance
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260409

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yld, Type I, 5 mm/min	81	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	78	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	3.2	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	3.5	%	ASTM D638
Tensile Modulus, 5 mm/min	4320	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	132	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	4100	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	81	MPa	ISO 527
Tensile Stress, break, 5 mm/min	78	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.1	%	ISO 527
Tensile Strain, break, 5 mm/min	3.5	%	ISO 527
Tensile Modulus, 1 mm/min	4320	MPa	ISO 527
Flexural Strength, 2 mm/min	128	MPa	ISO 178
Flexural Modulus, 2 mm/min	3900	MPa	ISO 178
IMPACT [1]			
Izod Impact, notched, 23°C	120	J/m	ASTM D256
Izod Impact, notched, -30°C	62	J/m	ASTM D256
Izod Impact, unnotched, 23°C	680	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	755	J/m	ASTM D4812
Instrumented Dart Impact Total Energy, 23°C	23	J	ASTM D3763
Instrumented Dart Impact Energy @ peak, 23°C	5	J	ASTM D3763
Izod Impact, notched 80*10*3 +23°C	12	kJ/m²	ISO 180/1A

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*3 -30°C	7	kJ/m²	ISO 180/1A
Izod Impact, unnotched 80*10*3 +23°C	41	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	43	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	11	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	7	kJ/m²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	42	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	44	kJ/m²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	11	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	6	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	47	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	51	kJ/m²	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	11	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	6	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	50	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	51	kJ/m²	ISO 179/1eU
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	120	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	114	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	119	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	113	°C	ISO 75/Af
CTE, 23°C to 80°C, flow	3.7E-5	1/°C	ASTM E831
CTE, 23°C to 80°C, xflow	7.6E-5	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	3.1E-5	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	5.4E-5	1/°C	ASTM E831
CTE, 23°C to 80°C, flow	3.9E-5	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.6E-5	1/°C	ISO 11359-2
CTE, -40°C to 40°C, flow	3.2E-5	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	5.9E-5	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	121	°C	ISO 306
Vicat Softening Temp, Rate B/120	123	°C	ISO 306
Relative Temp Index, Elec [2]	80	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	80	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	80	°C	UL 746B
PHYSICAL [1]			
Specific Gravity	1.27	-	ASTM D792
Melt Flow Rate			
300°C/1.2 kgf	13	g/10 min	ASTM D1238
300°C/2.16 kgf	27.7	g/10 min	ASTM D1238
Melt Volume Rate			
300°C/1.2 kg	12	cm³/10 min	ISO 1133
300°C/2.16 kg	25.2	cm³/10 min	ISO 1133
Water Absorption, (23°C/24hrs)	0.04	%	ISO 62-1
Mold Shrinkage, flow [3]	0.32	%	SABIC method
Mold Shrinkage, xflow [3]	0.42	%	SABIC method
ELECTRICAL [1]			

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Surface Resistivity	1.E+16	Ω	ASTM D257
Volume Resistivity	1.E+16	Ω.cm	ASTM D257
Dielectric Constant			
1.1 GHz	3	-	SABIC method
1.9 GHz	3.05	-	SABIC method
5 GHz	3.04	-	SABIC method
10 GHz	2.99	-	SABIC method
Dissipation Factor			
1.1 GHz	0.007	-	SABIC method
1.9 GHz	0.007	-	SABIC method
5 GHz	0.007	-	SABIC method
10 GHz	0.007	-	SABIC method
FLAME CHARACTERISTICS (2)			
UL Yellow Card Link	E207780-104529301	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.8	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥0.6	mm	UL 94
INJECTION MOLDING (4)			
Drying Temperature	110	°C	
Drying Time	3 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	285 – 310	°C	
Nozzle Temperature	285 – 305	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.1 – 0.3	MPa	
Screw Speed	50 – 90	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved