ULTEM™ Resin HU1110

REGION AMERICAS

DESCRIPTION

Enhanced flow Polyetherimide (Tg 217C). ECO Conforming. For medical devices and pharmaceutical applications. Healthcare management of change; biocompatible (ISO 10993 or USP Class VI); Steam, Gamma, EtO, and E-beam sterilizable.

This material is food contact compliant in most jurisdictions – exceptions may exist, request a declaration for details.

GENERAL INFORMATION	
Features	Flame Retardant, Chemical Resistance, Good Processability, High Flow, Hydrolytic Stability, Low Warpage, Thin Wall, Amorphous, Low Shrinkage, Low Moisture Absorption, UV-C resistant, Bio-Renewable, Biocompatability-ISO10993, Food contact, Healthcare/Formula lock, Non Cl/Br flame retardant, Non halogenated flame retardant, Autoclave/Steam sterilizable, Creep resistant, Dimensional stability, High stiffness/Strength, High temperature resistance, Sterilizable, No PFAS intentionally added, Additive Manufacturing
Fillers	Unreinforced
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Hygiene and Healthcare	Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing

TYPICAL PROPERTY VALUES

Revision 20250404

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	110	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	85	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	70	%	ASTM D638
Tensile Modulus, 5 mm/min	3720	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	174	MPa	ASTM D790
Flexural Stress, yld, 2.6 mm/min, 100 mm span	165	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3420	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	3720	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	110	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6	%	ISO 527
Tensile Strain, break, 5 mm/min	60	%	ISO 527
Tensile Modulus, 1 mm/min	3500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	140	MPa	ISO 178
Flexural Modulus, 2 mm/min	3300	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	56	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	1922	J/m	ASTM D256
Gardner, 23°C	23	J	ASTM D3029

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Instrumented Dart Impact Total Energy, 23°C	28	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	4	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	4	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	5	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	219	°C	ASTM D1525
HDT, 1.82 MPa, 6.4 mm, unannealed	198	°C	ASTM D648
CTE, -40°C to 40°C, flow	5.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	5.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	5.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	5.5E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	200	°C	ISO 306
Vicat Softening Temp, Rate B/120	205	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	210	°C	ISO 75/Af
Relative Temp Index, Elec [1]	170	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	170	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	170	°C	UL 746B
PHYSICAL			
Specific Gravity	1.36	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	16	g/10 min	ASTM D1238
Density	1.36	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	1.2	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.65	%	ISO 62
Melt Volume Rate, MVR at 360°C/5.0 kg	21	cm³/10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥0.75	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥3	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥0.75	mm	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D495
FLAME CHARACTERISTICS [1]			
UL Yellow Card Link	E121562-100044748	-	-
UL Recognized, 94-5VA Flame Class Rating	≥3	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥0.75	mm	UL 94
UL Recognized, 94V-2 Flame Class Rating	≥0.4	mm	UL 94
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved