

LNPTTM THERMOCOMPTM COMPOUND YF003S

YF-1003 HS

DESCRIPTION

LNP THERMOCOMP YF003S compound is based on Thermoplastic Polyester Elastomer (TPE) resin containing 15% glass fiber. Added features of this grade include: Heat Stabilized.

GENERAL INFORMATION	
Features	Heat Stabilized, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Thermoplastic Polyester Elastomer (TPEE)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport / Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 50 mm/min	43	MPa	ISO 527
Tensile Stress, break, 50 mm/min	42	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	15	%	ISO 527
Tensile Modulus, 1 mm/min	1500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	45	MPa	ISO 178
Flexural Modulus, 2 mm/min	1200	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	85	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	28	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	3.4E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.95E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	163	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	121	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow ⁽²⁾	0.5	%	SABIC method
Density	1.3	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.54	%	ISO 62-1
INJECTION MOLDING ⁽³⁾			
Drying Temperature	80	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4	Hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	215 – 240	°C	
Front - Zone 3 Temperature	225 – 240	°C	
Middle - Zone 2 Temperature	205 – 215	°C	
Rear - Zone 1 Temperature	180 – 195	°C	
Mold Temperature	25 – 55	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.