

LNPTTM THERMOCOMPTM COMPOUND LC008EXP

DESCRIPTION

LNP THERMOCOMP LC008EXP compound is based on Polyetheretherketone (PEEK) resin containing 40% carbon fiber. Added features of this grade include: Electrically Conductive, Easy Molding.

GENERAL INFORMATION	
Features	Electrically Conductive, Good Processability, Carbon fiber filled, High stiffness/Strength, High temperature resistance
Fillers	Carbon Fiber
Polymer Types	Polyetheretherketone (PEEK)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical, Material Handling

TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	256	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.6	%	ISO 527
Tensile Modulus, 1 mm/min	26200	MPa	ISO 527
Flexural Stress, break, 2 mm/min	341	MPa	ISO 178
Flexural Modulus, 2 mm/min	22900	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	45	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	4.E-06	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	4.1E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	>300	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.45	g/cm ³	ISO 1183
INJECTION MOLDING ⁽²⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.1	%	
Melt Temperature	380 – 390	°C	
Front - Zone 3 Temperature	380 – 395	°C	
Middle - Zone 2 Temperature	365 – 375	°C	
Rear - Zone 1 Temperature	350 – 360	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	140 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.