LNP™ FARADEX™ Compound DS0036I

DS-1003 FR HI
REGION AMERICAS

DESCRIPTION

LNP FARADEX DS0036I compound is based on Polycarbonate (PC) resin containing 15% stainless steel fiber. Added features of this grade include: Electrically Conductive, EMI/RFI shielding, High Impact, Non-Brominated & Non-Chlorinated Flame Retardant.

GENERAL INFORMATION	
Features	Flame Retardant, Electrically Conductive, EMI/RFI Shielding, Non Cl/Br flame retardant, Impact resistant
Fillers	Stainless Steel Fiber
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components
Industrial	Electrical, Material Handling
Packaging	Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20261113

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yield	57	MPa	ISO 527
Tensile Stress, break	55	MPa	ISO 527
Tensile Strain, yield	3.8	%	ISO 527
Tensile Strain, break	4 – 8	%	ISO 527
Tensile Modulus, 1 mm/min	2800	MPa	ISO 527
Flexural Stress	80	MPa	ISO 178
Flexural Modulus	2600	MPa	ISO 178
IMPACT [1]			
Izod Impact, Unnotched			
23°C	1790	J/m	ASTM D4812
80*10*4 +23°C	85	kJ/m²	ISO 180/1U
Izod impact, notched			
23°C	124	J/m	ASTM D256
80*10*4 +23°C	14	kJ/m²	ISO 180/1A
THERMAL [1]			
CTE, -40°C to 40°C, flow	5.60E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.70E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	136	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	125	°C	ISO 75/Af

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL [1]			
Mold Shrinkage, flow, 24 hrs [2]	0.4 – 0.7	%	ISO 294
Mold Shrinkage, xflow, 24 hrs [2]	0.5	%	ISO 294
Density	1.29	g/cm³	ISO 1183
ELECTRICAL [1]			
Volume Resistivity [3]	1.E+04	Ω.cm	ASTM D257
Surface Resistivity [3]	1.E+02 – 1.E+04	Ω	ASTM D257
Shielding Effectivness @ 3mm	40 – 55	dB	SABIC method
INJECTION MOLDING [4]			
Drying Temperature	120	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	95 – 120	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Measurement meets requirements as specified in ASTM D4496.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved