

LNPT[™] THERMOCOMP[™] COMPOUND RC008XXQ

DESCRIPTION

LNP THERMOCOMP RC008XXQ compound is based on Nylon 6/6 resin containing 40% carbon fiber. Added features of this grade include: Electrically Conductive.

| GENERAL INFORMATION | |
|-----------------------|--|
| Features | Electrically Conductive, Carbon fiber filled, High stiffness/Strength, No PFAS intentionally added |
| Fillers | Carbon Fiber |
| Polymer Types | Polyamide 66 (Nylon 66) |
| Processing Techniques | Injection Molding |

| INDUSTRY | SUB INDUSTRY |
|---------------------------|--|
| Automotive | Aerospace |
| Building and Construction | Building Component |
| Consumer | Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance |

TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|-----------------|-------|--------------|
| MECHANICAL ⁽¹⁾ | | | |
| Tensile Stress, brk, Type I, 5 mm/min | 315 | MPa | ASTM D638 |
| Tensile Strain, brk, Type I, 5 mm/min | 1.3 | % | ASTM D638 |
| Tensile Modulus, 5 mm/min | 40000 | MPa | ASTM D638 |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 488 | MPa | ASTM D790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 30100 | MPa | ASTM D790 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, unnotched, 23°C | 976 | J/m | ASTM D4812 |
| Izod Impact, notched, 23°C | 105 | J/m | ASTM D256 |
| THERMAL ⁽¹⁾ | | | |
| HDT, 1.82 MPa, 3.2mm, unannealed | 257 | °C | ASTM D648 |
| PHYSICAL ⁽¹⁾ | | | |
| Specific Gravity | 1.32 | - | ASTM D792 |
| ELECTRICAL ⁽¹⁾ | | | |
| Surface Resistivity | 1.E+01 – 1.E+02 | Ω | ASTM D257 |
| INJECTION MOLDING ⁽²⁾ | | | |
| Drying Temperature | 80 | °C | |
| Drying Time | 4 | Hrs | |
| Maximum Moisture Content | 0.15 – 0.25 | % | |
| Melt Temperature | 280 – 305 | °C | |
| Front - Zone 3 Temperature | 295 – 305 | °C | |
| Middle - Zone 2 Temperature | 280 – 295 | °C | |
| Rear - Zone 1 Temperature | 265 – 275 | °C | |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|------------------|----------------|-------|--------------|
| Mold Temperature | 95 – 110 | °C | |
| Back Pressure | 0.2 – 0.3 | MPa | |
| Screw Speed | 30 – 60 | rpm | |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.