LNP™ THERMOCOMP™ Compound GF004

GF-1004
REGION ASIA

DESCRIPTION

LNP THERMOCOMP GF004 compound is based on Polysulfone (PSU) resin containing 20% glass fiber.

GENERAL INFORMATION	
Features	High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polysulfone (PSU)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical, Defense

TYPICAL PROPERTY VALUES

Revision 20260204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yield	91	MPa	ASTM D638
Tensile Stress, break	91	MPa	ASTM D638
Tensile Strain, yield	2.3	%	ASTM D638
Tensile Strain, break	2.3	%	ASTM D638
Tensile Modulus, 50 mm/min	6200	MPa	ASTM D638
Flexural Stress	137	MPa	ASTM D790
Flexural Modulus	6200	MPa	ASTM D790
Flexural Stress	145	MPa	ISO 178
Flexural Modulus	6000	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched, 23°C	427	J/m	ASTM D4812
Izod Impact, notched, 23°C	53	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	10	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	31	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m²	ISO 180/1A
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	178	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	173	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.52E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	5.22E-05	1/°C	ASTM E831

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	2.50E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	5.20E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	180	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	174	°C	ISO 75/Af
PHYSICAL [1]			
Density	1.41	g/cm³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.1	%	ASTM D570
Mold Shrinkage, flow, 24 hrs [2]	0.6	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs [2]	0.9	%	ASTM D955
Mold Shrinkage, flow, 24 hrs [2]	0.64	%	ISO 294
Mold Shrinkage, xflow, 24 hrs [2]	0.85	%	ISO 294
Density	1.4	g/cm³	ISO 1183

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved