

# LNPTM LUBRICOMP™ COMPOUND NL001

PCA-L-4010

REGION EUROPE

## DESCRIPTION

LNP LUBRICOMP NL001 compound is based on Polycarbonate / Acrylonitrile Butadiene Styrene (PC/ABS) blend containing 5% PTFE. Added features of this grade include: Wear Resistant, targeted for Thin Wall applications.

GENERAL INFORMATION	
Features	Wear resistant, Thin Wall
Fillers	Unreinforced, PTFE
Polymer Types	Polycarbonate + ABS (PC+ABS)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 50 mm/min	53	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	43	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	3.6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	24.3	%	ASTM D638
Tensile Modulus, 50 mm/min	2400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	86	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2440	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	45	MPa	ISO 527
Tensile Stress, break, 5 mm/min	40	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	45	%	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	20	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 +23°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	13	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	116	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	99	°C	ASTM D648
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.7E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Ball Pressure Test, approximate maximum	100	°C	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	113	°C	ISO 306
Vicat Softening Temp, Rate B/120	115	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	95	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	114	°C	ISO 75/Bf
Relative Temp Index, Elec <sup>(2)</sup>	60	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	60	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	60	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.14	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow <sup>(3)</sup>	0.5 – 0.7	%	SABIC method
Density	1.1	g/cm <sup>3</sup>	ISO 1183
Melt Volume Rate, MVR at 260°C/5.0 kg	26	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E45329-101344461</a>	-	-
UL Recognized, 94HB Flame Class Rating	≥0.75	mm	UL 94
Oxygen Index (LOI)	21	%	ISO 4589
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	90 – 100	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	240 – 270	°C	
Nozzle Temperature	220 – 260	°C	
Front - Zone 3 Temperature	230 – 270	°C	
Middle - Zone 2 Temperature	230 – 270	°C	
Rear - Zone 1 Temperature	210 – 240	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 90	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.