LNP™ THERMOCOMP™ Compound LF006EX1

DESCRIPTION

LNP THERMOCOMP LF006EX1 compound is based on Polyetheretherketone (PEEK) resin containing 30% glass fiber. Added features of this grade include: Low warpage, Easy Molding.

GENERAL INFORMATION	
Features	Good Processability, Low Warpage, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polyetheretherketone (PEEK)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical, Material Handling

TYPICAL PROPERTY VALUES

Revision 20260408

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, brk, Type I, 5 mm/min	170	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.3	%	ASTM D638
Tensile Modulus, 5 mm/min	12300	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	235	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	10100	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	170	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	11800	MPa	ISO 527
Flexural Strength, 2 mm/min	225	MPa	ISO 178
Flexural Modulus, 2 mm/min	10200	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched, 23°C	732	J/m	ASTM D4812
Izod Impact, notched, 23°C	95	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	47	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m²	ISO 180/1A
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	46	kJ/m²	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	10	kJ/m²	ISO 179/1eA
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	336	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	321	°C	ASTM D648
CTE			

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
-40°C to 120°C, flow	2.23E-5	1/°C	ASTM E831
-40°C to 120°C, xflow	4.10E-05	1/°C	ASTM E831
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	333	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	309	°C	ISO 75/Af
PHYSICAL (1)			
Moisture Absorption, (23°C/50% RH/24 hrs)	0.037	%	ASTM D570
Specific Gravity	1.536	-	ASTM D792
Mold Shrinkage, flow (2)	0.43	%	SABIC method
Mold Shrinkage, xflow (2)	0.65	%	SABIC method
Moisture Absorption, (23°C/50% RH/Equilibrium)	0.088	%	ISO 62-4
Density	1.532	g/cm³	ASTM D792
ELECTRICAL (1)			
Dielectric Constant			
1.1 GHz	3.82	-	SABIC method
1.9 GHz	3.84	-	SABIC method
Dissipation Factor			
1.1 GHz	0.0039	-	SABIC method
1.9 GHz	0.0041	-	SABIC method
INJECTION MOLDING (3)			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Front - Zone 3 Temperature	380 – 400	°C	
Middle - Zone 2 Temperature	380 – 400	°C	
Rear - Zone 1 Temperature	370 – 380	°C	
Mold Temperature	175 – 190	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved