LNP™ THERMOCOMP™ Compound UX06028

UF-1008 A MR

DESCRIPTION

LNP THERMOCOMP UX06028 compound is based on Polyphthalamide (PPA) resin containing 40% glass fiber. Added features of this grade include: Mold Release.

GENERAL INFORMATION	
Features	Enhanced mold release, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polyphthalamide (PPA)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Under the Hood
Consumer	Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, break, 5 mm/min	234	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.1	%	ISO 527
Tensile Modulus, 1 mm/min	14500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	315	MPa	ISO 178
Flexural Modulus, 2 mm/min	12000	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched 80*10*4 +23°C	55	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m²	ISO 180/1A
THERMAL [1]			
CTE, 23°C to 60°C, flow	2.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	5.3E-05	1/°C	ISO 11359-2
PHYSICAL [1]			
Mold Shrinkage, flow [2]	0.14	%	SABIC method
Density	1.53	g/cm³	ISO 1183
FLAME CHARACTERISTICS [3]			
UL Yellow Card Link	E45329-101284057	-	-
UL Recognized, 94HB Flame Class Rating	0.8	mm	UL 94
INJECTION MOLDING [4]			
Drying Temperature	120 – 150	°C	

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4	Hrs	
Maximum Moisture Content	0.15	%	
Melt Temperature	315 – 330	°C	
Front - Zone 3 Temperature	325 – 340	°C	
Middle - Zone 2 Temperature	315 – 325	°C	
Rear - Zone 1 Temperature	310 – 320	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved