

NORYL™ RESIN PKN4752

REGION ASIA

DESCRIPTION

NORYL PKN4752 resin is a non-reinforced, translucent, high heat blend of polyphenylene ether (PPE) + general purpose polystyrene (GPPS). This extrudable and injection moldable grade exhibits high heat resistance, dimensional stability, and appears translucent with a yellow tint in the natural color. NORYL PKN4752 resin is an excellent candidate for high performance packaging in food, electronics, and healthcare. *See NORYL PKN4752F resin for FDA food compliant version.

GENERAL INFORMATION	
Features	Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Transparent/Translucent, Dimensional stability, High temperature resistance
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + General Purpose PS (PPE+GPPS)
Processing Techniques	Sheet extrusion, Profile Extrusion

INDUSTRY	SUB INDUSTRY
Industrial	Material Handling
Packaging	Industrial Packaging

TYPICAL PROPERTY VALUES

Revision 20241016

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	86	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	73	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	15	%	ASTM D638
Tensile Modulus, 50 mm/min	3000	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	144	MPa	ASTM D790
Flexural Stress, yld, 2.6 mm/min, 100 mm span	136	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3150	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	2940	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	32	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	6	J	ASTM D3763
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	173	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	160	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	151	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	151	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.3E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	5.58E-05	1/°C	ASTM E831
PHYSICAL ⁽¹⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Specific Gravity	1.08	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.6 – 0.9	%	SABIC method
SHEET EXTRUSION			
Drying Temperature	70 – 80	°C	
Drying Time	2 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0	%	
Melt Temperature	265 – 275	°C	
Barrel - Zone 1 Temperature	205 – 225	°C	
Barrel - Zone 2 Temperature	215 – 240	°C	
Barrel - Zone 3 Temperature	240 – 265	°C	
Barrel - Zone 4 Temperature	240 – 265	°C	
Adapter Temperature	240 – 265	°C	
Die Temperature	240 – 265	°C	
Roll Stack Temp - Top	105 – 120	°C	
Roll Stack Temp - Middle	105 – 120	°C	
Roll Stack Temp - Bottom	105 – 120	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.