

LNPT[™] ELCREST[™] DMX1233

DESCRIPTION

LNP ELCRES DMX1233 is a UV stabilized improved flow Polycarbonate (PC) copolymer resin. Available in both transparent and custom colours, this grade is a good candidate for 5G related devices, anti-scratch covers etc. Added features of this grade include: Improved Scratch Resistance and Improved Dielectric Performance (lower Df).

| GENERAL INFORMATION | |
|----------------------------|--|
| Features | Good Processability, Dielectrics, Amorphous, IR Transparent, Scratch Resistance, Transparent/Translucent, Weatherable/UV stable, No PFAS intentionally added |
| Fillers | Unreinforced |
| Polymer Types | Polycarbonate (PC) |
| Processing Techniques | Injection Molding |
| INDUSTRY | SUB INDUSTRY |
| Automotive | Automotive Interiors |
| Consumer | Personal Accessory |
| Electrical and Electronics | Electronic Components |
| Industrial | Electrical |

TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------|--------------|
| MECHANICAL ⁽¹⁾ | | | |
| Tensile Stress, brk, Type I, 50 mm/min | 58.4 | MPa | ASTM D638 |
| Tensile Strain, brk, Type I, 50 mm/min | 42.3 | % | ASTM D638 |
| Tensile Modulus, 50 mm/min | 2505 | MPa | ASTM D638 |
| Flexural Strength, 1.3 mm/min, 50 mm span | 108 | MPa | ASTM D790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 2340 | MPa | ASTM D790 |
| Tensile Stress, break, 50 mm/min | 56.5 | MPa | ISO 527 |
| Tensile Strain, break, 50 mm/min | 29.9 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 2384 | MPa | ISO 527 |
| Flexural Strength, 2 mm/min | 104 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 2303 | MPa | ISO 178 |
| Pencil Hardness test, 1kgf | HB | - | ASTM D3363 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, notched, 23°C | 45 | J/m | ASTM D256 |
| Izod Impact, unnotched, 23°C | NB | J/m | ASTM D4812 |
| Izod Impact, notched 80*10*4 +23°C | 4.37 | kJ/m ² | ISO 180/1A |
| Izod Impact, unnotched 80*10*4 +23°C | NB | kJ/m ² | ISO 180/1U |
| Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm | 3 | kJ/m ² | ISO 179/1eA |
| Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm | NB | kJ/m ² | ISO 179/1eU |
| THERMAL ⁽¹⁾ | | | |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 134 | °C | ASTM D648 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|-----------------------------------|----------|--------------|
| HDT, 1.82 MPa, 3.2mm, unannealed | 121 | °C | ASTM D648 |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 133 | °C | ISO 75/Bf |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 117 | °C | ISO 75/Af |
| CTE | | | |
| -40°C to 80°C, flow | 7.5E-5 | 1/°C | ISO 11359-2 |
| -40°C to 80°C, xflow | 8.1E-5 | 1/°C | ISO 11359-2 |
| Vicat Softening Temp, Rate A/50 | 146 | °C | ASTM D1525 |
| Vicat Softening Temp, Rate B/50 | 139 | °C | ISO 306 |
| Relative Temp Index, Elec ⁽²⁾ | 80 | °C | UL 746B |
| Relative Temp Index, Mech w/impact ⁽²⁾ | 80 | °C | UL 746B |
| Relative Temp Index, Mech w/o impact ⁽²⁾ | 80 | °C | UL 746B |
| PHYSICAL ⁽¹⁾ | | | |
| Specific Gravity | 1.1827 | - | ASTM D792 |
| Water Absorption, (23°C/24hrs) | 0.037 | % | ASTM D570 |
| Melt Flow Rate, 300°C/1.2 kgf | 21 | g/10 min | ASTM D1238 |
| Mold Shrinkage, flow ⁽³⁾ | 0.73 | % | SABIC method |
| Mold Shrinkage, xflow ⁽³⁾ | 0.72 | % | SABIC method |
| ELECTRICAL ⁽¹⁾ | | | |
| Dielectric Constant, 1.1 GHz | 2.76 | - | SABIC method |
| Dissipation Factor, 1.1 GHz | 0.0037 | - | SABIC method |
| Dielectric Constant, 1.9 GHz | 2.77 | - | SABIC method |
| Dissipation Factor, 1.9 GHz | 0.0035 | - | SABIC method |
| Dielectric Constant, 5 GHz | 2.77 | - | SABIC method |
| Dissipation Factor, 5 GHz | 0.0032 | - | SABIC method |
| Dielectric Constant, 10 GHz | 2.87 | - | SABIC method |
| Dissipation Factor, 10 GHz | 0.0033 | - | SABIC method |
| Dielectric Constant, 20 GHz | 2.73 | - | SABIC method |
| Dissipation Factor, 20 GHz | 0.0035 | - | SABIC method |
| FLAME CHARACTERISTICS ⁽²⁾ | | | |
| UL Yellow Card Link | E207780-104568852 | - | - |
| UL Recognized, 94HB Flame Class Rating | ≥0.6 | mm | UL 94 |
| INJECTION MOLDING ⁽⁴⁾ | | | |
| Drying Temperature | 110 – 120 | °C | |
| Drying Time | 3 – 4 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 295 – 315 | °C | |
| Nozzle Temperature | 290 – 310 | °C | |
| Front - Zone 3 Temperature | 295 – 315 | °C | |
| Middle - Zone 2 Temperature | 280 – 305 | °C | |
| Rear - Zone 1 Temperature | 260 – 280 | °C | |
| Mold Temperature | 70 – 95 | °C | |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.