

LNPT[™] LUBRICOMP[™] COMPOUND OCL36A

OCL-4036 HI FLOW

REGION EUROPE

DESCRIPTION

LNP LUBRICOMP OCL36A compound is based on Polyphenylene Sulfide (PPS) - branched resin containing 30% carbon fiber, 15% PTFE. Added features of this grade include: Electrically Conductive, Wear Resistant.

GENERAL INFORMATION	
Features	Electrically Conductive, Wear resistant, Carbon fiber filled, High stiffness/Strength
Fillers	Carbon Fiber, PTFE
Polymer Types	Polyphenylene Sulfide, Branched (PPS, Branched)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break, 5 mm/min	153	MPa	ISO 527
Tensile Strain, break, 5 mm/min	0.7	%	ISO 527
Tensile Modulus, 1 mm/min	25000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	261	MPa	ISO 178
Flexural Stress, break, 2 mm/min	217	MPa	ISO 178
Flexural Strain, break, 2 mm/min	1.3	%	ISO 178
Flexural Modulus, 2 mm/min	21200	MPa	ISO 178
Flexural Strain, break, 2 mm/min, 80°C	1.3	%	ISO 178
Flexural Strain, break, 2 mm/min, 120°C	2.3	%	ISO 178
Flexural Strain, break, 2 mm/min, 150°C	2.4	%	ISO 178
Flexural Strain, break, 2 mm/min, 200°C	2.4	%	ISO 178
Flexural Stress, yield, 2 mm/min, 80°C	212	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 120°C	118	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 150°C	94	MPa	ISO 178
Flexural Stress, yield, 2 mm/min, 200°C	66	MPa	ISO 178
Flexural Modulus, 2 mm/min, 80°C	20600	MPa	ISO 178
Flexural Modulus, 2 mm/min, 120°C	10200	MPa	ISO 178
Flexural Modulus, 2 mm/min, 150°C	7900	MPa	ISO 178
Flexural Modulus, 2 mm/min, 200°C	6100	MPa	ISO 178

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*3 -40°C	6	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	26	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -40°C	23	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
Specific Heat	1633	J/kg-K	ASTM E1269
CTE, 23°C to 60°C, flow	3.E-06	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	4.9E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	278	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	255	°C	ISO 75/Af
Thermal Conductivity	0.36	W/m-K	ASTM D5930
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow, 24 hrs ⁽²⁾	0.19	%	ISO 294
Mold Shrinkage, xflow, 24 hrs ⁽²⁾	0.95	%	ISO 294
Wear Factor Washer	19	10 ⁻¹⁰ in ⁴ 5-min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.39	-	ASTM D3702 Modified: Manual
Density	1.52	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.05	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62
Melt Volume Rate, MVR at 315°C/5.0 kg	4 – 6	cm ³ /10 min	ISO 1133
ELECTRICAL ⁽¹⁾			
Surface Resistivity	1.E+01 – 1.E+03	Ω	ASTM D257
INJECTION MOLDING ⁽³⁾			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Melt Temperature	315 – 320	°C	
Front - Zone 3 Temperature	330 – 345	°C	
Middle - Zone 2 Temperature	320 – 330	°C	
Rear - Zone 1 Temperature	305 – 315	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.