

LNPT[™] LUBRICOMP[™] COMPOUND SFL36

SFL-4036

DESCRIPTION

LNP LUBRICOMP SFL36 compound is based on Nylon 12 resin containing 30% glass fiber, 15% PTFE. Added features of this grade include: Internally Lubricated, Wear Resistant.

GENERAL INFORMATION	
Features	Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, PTFE
Polymer Types	Polyamide 12 (Nylon 12)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Under the Hood
Consumer	Home Appliances, Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 5 mm/min	100	MPa	ISO 527
Tensile Strain, break, 5 mm/min	4.5	%	ISO 527
Flexural Stress, yield, 2 mm/min	147	MPa	ISO 178
Flexural Modulus, 2 mm/min	5900	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	65	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	15	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
CTE, 23°C to 60°C, flow	2.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.17E-04	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	175	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	160	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	65	°C	UL 746B
PHYSICAL ⁽¹⁾			
Mold Shrinkage, flow ⁽³⁾	0.1 – 0.3	%	SABIC method
Density	1.37	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.14	%	ISO 62-1
FLAME CHARACTERISTICS ⁽²⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Yellow Card Link	E45329-101284435	-	-
UL Recognized, 94HB Flame Class Rating	0.75	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.12 – 0.2	%	
Melt Temperature	225 – 240	°C	
Front - Zone 3 Temperature	225 – 240	°C	
Middle - Zone 2 Temperature	220 – 230	°C	
Rear - Zone 1 Temperature	215 – 225	°C	
Mold Temperature	70 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.