LNP™ THERMOCOMP™ Compound DX06313I

DESCRIPTION

LNP THERMOCOMP DX06313I compound is based on Polycarbonate (PC) resin containing 30% glass fiber. Added features of this grade include: Impact Modified, Thin-Wall Molding, Improved Flow.

GENERAL INFORMATION	
Features	Thin Wall, High stiffness/Strength, Impact resistant, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Mobile Phone - Computer - Tablets

TYPICAL PROPERTY VALUES

Revision 20240715

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, brk, Type I, 5 mm/min	105	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.7	%	ASTM D638
Tensile Modulus, 5 mm/min	7900	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	170	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7500	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	115	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.6	%	ISO 527
Tensile Modulus, 1 mm/min	8300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	175	MPa	ISO 178
Flexural Modulus, 2 mm/min	7200	MPa	ISO 178
IMPACT [1]			
Izod Impact, notched, 23°C	160	J/m	ASTM D256
Izod Impact, notched, -30°C	130	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	25	J	ASTM D3763
Izod Impact, unnotched 80*10*3 +23°C	54	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	50	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	18	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	14	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	17	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	15	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	65	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	55	kJ/m²	ISO 179/1eU
THERMAL [1]			
Vicat Softening Temp, Rate B/50	142	°C	ASTM D1525

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	136	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.2E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	2.2E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	142	°C	ISO 306
Vicat Softening Temp, Rate B/120	143	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	136	°C	ISO 75/Af
Relative Temp Index, Elec (2)	80	°C	UL 746B
Relative Temp Index, Mech w/impact (2)	80	°C	UL 746B
Relative Temp Index, Mech w/o impact (2)	80	°C	UL 746B
PHYSICAL (1)			
Specific Gravity	1.42	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm (3)	0.3 – 0.5	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	30	g/10 min	ASTM D1238
Density	1.42	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.4	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.1	%	ISO 62
Melt Volume Rate, MVR at 300°C/5.0 kg	22	cm³/10 min	ISO 1133
FLAME CHARACTERISTICS (2)			
UL Yellow Card Link	E207780-100120256	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
INJECTION MOLDING (4)			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 330	°C	
Nozzle Temperature	305 – 325	°C	
Front - Zone 3 Temperature	310 – 330	°C	
Middle - Zone 2 Temperature	300 – 320	°C	
Rear - Zone 1 Temperature	290 – 310	°C	
Mold Temperature	80 – 115	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

© 2026 Copyright by SABIC. All rights reserved

MORE INFORMATION

For curve data and CAE cards, please visit and register at https://materialfinder.sabic-specialties.com

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved