

ULTEM™ RESIN 1010UCL

DESCRIPTION

ULTEM 1010UCL resin is an amorphous, transparent polyetherimide (PEI) thermoplastic offering enhanced flow and a glass transition temperature (Tg) of 217°C. 1010UCL offers the same performance as ULTEM 1010 resin and offers further enhanced cleanliness control for (optical) applications.

The natural (uncolored) version of this grade is compliant with RoHS and also with Halogen Free standards as IEC 61249-2-21 and e.g. IPC 4101E. For colored versions, compliance needs to be checked case by case.

GENERAL INFORMATION	
Features	Flame Retardant, Chemical Resistance, Good Processability, High Flow, Hydrolytic Stability, Low Warpage, Low Smoke and Toxicity, Thin Wall, Dielectrics, Amorphous, Low Shrinkage, IR Transparent, Transparent/Translucent, Electroplatable, Creep resistant, Dimensional stability, High stiffness/Strength, High temperature resistance
Fillers	Unreinforced
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Injection Molding
Regional Availability	Europe, Asia, Americas

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Mobile Phone - Computer - Tablets, Wireless Communication
Industrial	Electrical, Eyewear

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 50 mm/min	105	MPa	ISO 527
Tensile Stress, break, 50 mm/min	85	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	60	%	ISO 527
Tensile Modulus, 1 mm/min	3200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	160	MPa	ISO 178
Flexural Modulus, 2 mm/min	3300	MPa	ISO 178
Ball Indentation Hardness, H358/30	140	MPa	ISO 2039-1
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	SABIC method
Tensile Stress, yld, Type I, 5 mm/min	110	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	60	%	ASTM D638
Tensile Modulus, 5 mm/min	3580	MPa	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	165	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	3510	MPa	ASTM D790
Hardness, Rockwell M	109	-	ASTM D785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D1044
IMPACT ⁽¹⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m ²	ISO 180/1A
Izod Impact, unnotched, 23°C	1335	J/m	ASTM D4812
Izod Impact, notched, 23°C	32	J/m	ASTM D256
Izod Impact, Reverse Notched, 3.2 mm	1174	J/m	ASTM D256
Gardner, 23°C	33	J	ASTM D3029
THERMAL ⁽¹⁾			
Thermal Conductivity	0.21	W/m·°C	ISO 8302
CTE, 23°C to 150°C, flow	5.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	5.2E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	215	°C	ISO 306
Vicat Softening Temp, Rate B/50	211	°C	ISO 306
Vicat Softening Temp, Rate B/120	212	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	200	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	190	°C	ISO 75/Ae
Vicat Softening Temp, Rate B/50	218	°C	ASTM D1525
HDT, 0.45 MPa, 6.4 mm, unannealed	207	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	198	°C	ASTM D648
CTE, -20°C to 150°C, flow	5.2E-05	1/°C	ASTM E831
Thermal Conductivity	0.22	W/m·°C	ASTM C177
PHYSICAL ⁽¹⁾			
Density	1.27	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	1.25	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.7	%	ISO 62
Melt Volume Rate, MVR at 340°C/5.0 kg	13	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 360°C/5.0 kg	25	cm ³ /10 min	ISO 1133
Specific Gravity	1.27	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.25	%	ASTM D570
Water Absorption, (23°C/Saturated)	1.25	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	17.8	g/10 min	ASTM D1238
OPTICAL ⁽¹⁾			
Light Transmission			
at 1.0 mm and 850 nm	88	%	ASTM D1003
at 1.0 mm and 1350 nm	89	%	ASTM D1003
Refractive Index			
at 850 nm	1.639	-	ISO 489
at 1350 nm	1.626	-	ISO 489
Abbe number	21	-	ISO 489
ELECTRICAL ⁽¹⁾			
Volume Resistivity	1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Strength, in oil, 0.8 mm	33	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.9	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0005	-	IEC 60250
Dissipation Factor, 1 MHz	0.006	-	IEC 60250
Dissipation Factor, 2450 MHz	0.0025	-	IEC 60250
Relative Permittivity, 50/60 Hz	2.9	-	IEC 60250
Volume Resistivity	1.E+17	Ω.cm	ASTM D257
Dielectric Strength, in air, 1.6 mm	32.7	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	28.0	kV/mm	ASTM D149
Relative Permittivity, 1 kHz	3.15	-	ASTM D150
Dissipation Factor, 1 kHz	0.0013	-	ASTM D150
Dissipation Factor, 2450 MHz	0.0025	-	ASTM D150
INJECTION MOLDING ⁽³⁾			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.