

# NORYL™ RESIN FNH2160

REGION ASIA

## DESCRIPTION

NORYL FNH2160 resin is a foamable blend of polyphenylene ether (PPE) + polystyrene (PS) and offers 20% weight reduction at 6.35mm (0.250") wall. This material contains non-brominated, non-chlorinated flame retardant with a UL94 flame rating of 5VA at 3.9 mm and V1 at 3mm. NORYL FNH2160 resin offers fast cycle time, improved processing, and exhibits good dimensional stability and low moisture absorption. The unique combination of properties in this structural foam material allows for designing optimum wall thickness in computer and business machine applications, electrical enclosures/housings, medical equipment, and hospital bed rails and components.

GENERAL INFORMATION	
Features	Flame Retardant, Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High stiffness/Strength
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Structural Foam Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Mobile Phone - Computer - Tablets
Hygiene and Healthcare	General Healthcare, Patient Testing

## TYPICAL PROPERTY VALUES

Revision 20241016

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Modulus, 50 mm/min	2680	MPa	ASTM D638
Tensile Stress, yield, 50 mm/min	55	MPa	ASTM D638
Tensile Strain, yield, 50 mm/min	3.04	%	ASTM D638
Tensile Stress, yield, 6.35 mm	36	MPa	ASTM D638
Tensile Stress, break, 6.35 mm	34	MPa	ASTM D638
Tensile Strain, break, 6.35 mm	12	%	ASTM D638
Flexural Stress, yield, 6.4 mm	70	MPa	ASTM D790
Flexural Modulus, 6.4 mm	2250	MPa	ASTM D790
FOAM - MECHANICAL 6.4 mm Wt Reduction	20	%	-
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched, 23°C, 6.4mm	362	J/m	ASTM D4812
Instrumented Dart Impact Energy @ peak, 23°C	29	J	ASTM D3763
FOAM - IMPACT 6.4 mm Wt Reduction	20	%	-
<b>THERMAL <sup>(1)</sup></b>			
FOAM - THERMAL 6.4mm Wt Reduction	20	%	-
HDT, 0.45 MPa, 6.4 mm, unannealed	93	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	82	°C	ASTM D648
Relative Temp Index, Elec <sup>(2)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	65	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	65	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
FOAM - PHYSICAL 6.4mm Wt Reduction	20	%	-
Specific Gravity	1.12	-	ASTM D792
Specific Gravity, foam molded	0.88	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.07	%	ASTM D570
Mold Shrinkage, flow, 6.4 mm <sup>(3)</sup>	0.5 – 0.8	%	SABIC method
Melt Volume Rate, MVR at 280°C/5.0 kg	36	cm <sup>3</sup> /10 min	ISO 1133
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-102274256</a>	-	-
FOAM - Flame Class Minimum Density	0.85	g/cm <sup>3</sup>	-
UL Recognized, 94-5VA Flame Class Rating	≥3.9	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥6	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥3	mm	UL 94
<b>STRUCTURAL FOAM MOLDING</b>			
Blowing Agent, Physical System	Nitrogen Gas	-	
Concentration Range (Blowing Agent)	1 – 3	%	
Recommended Concentration (Blowing Agent)	2	%	
Drying Temperature (Resin)	70 – 80	°C	
Drying Time (Resin)	2 – 4	Hrs	
Drying Time (Resin, Cumulative)	8	Hrs	
Melt Temperature	270 – 310	°C	
Nozzle Temperature	270 – 305	°C	
Front Temperature	270 – 305	°C	
Middle Temperature	270 – 305	°C	
Rear Temperature	230 – 260	°C	
Mold Temperature	25 – 55	°C	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.