

# VALOX™ FR RESIN VC108

## DESCRIPTION

VALOX VC108 compound is based on Polybutylene Terephthalate (PBT) resin containing 8% carbon fiber. Added features of this grade include: Electrically Conductive, Flame Retardant.

GENERAL INFORMATION	
Features	Flame Retardant, Electrically Conductive, Carbon fiber filled, High stiffness/Strength
Fillers	Carbon Fiber
Polymer Types	Polybutylene Terephthalate (PBT)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield	98	MPa	SABIC - Japan Method
Tensile Strain, break	3	%	SABIC - Japan Method
Flexural Stress	148	MPa	ASTM D790
Flexural Modulus	5980	MPa	ASTM D790
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	39	J/m	ASTM D256
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	199	°C	ASTM D648
CTE, -30°C to 30°C	8.00E-05	1/°C	TMA
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.43	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.07	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>	0.3 – 0.5	%	SABIC method
Mold Shrinkage, flow, 6.4 mm <sup>(2)</sup>	0.8 – 1	%	SABIC method
<b>ELECTRICAL <sup>(1)</sup></b>			
Surface Resistivity <sup>(3)</sup>	1.E+08 – 1.E+12	Ω	ASTM D257
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	235 – 255	°C	
Nozzle Temperature	230 – 250	°C	
Front - Zone 3 Temperature	235 – 255	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	230 – 250	°C	
Rear - Zone 1 Temperature	225 – 245	°C	
Mold Temperature	50 – 130	°C	
Back pressure (Plastic Pressure)	3 – 8	MPa	
Screw speed (Circumferential speed)	0.1 – 0.2	m/s	
Shot to Cylinder Size	30 – 70	%	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Measurement meets requirements as specified in ASTM D4496.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.