LNP™ THERMOCOMP™ COMPOUND LC006

LC-1006
REGION AMERICAS

DESCRIPTION

LNP THERMOCOMP LC006 compound is based on Polyetheretherketone (PEEK) resin containing 30% carbon fiber. Added features of this grade include: Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, High temperature resistance, No PFAS intentionally added
Fillers	Carbon Fiber
Polymer Types	Polyetheretherketone (PEEK)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical, Material Handling

TYPICAL PROPERTY VALUES

Revision 20260210

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, break	225	MPa	ASTM D638
Tensile Strain, break	1.5	%	ASTM D638
Tensile Modulus, 50 mm/min	30750	MPa	ASTM D638
Flexural Stress	325	MPa	ASTM D790
Flexural Modulus	20200	MPa	ASTM D790
Tensile Stress, break	230	MPa	ISO 527
Tensile Strain, break	1.5	%	ISO 527
Tensile Modulus, 1 mm/min	24050	MPa	ISO 527
Flexural Stress	346	MPa	ISO 178
Flexural Modulus	24300	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched, 23°C	608	J/m	ASTM D4812
Izod Impact, notched, 23°C	74	J/m	ASTM D256
Instrumented Dart Impact Energy @ peak, 23°C	12	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	44	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m²	ISO 180/1A
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	298	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	298	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.2E-05	1/°C	ASTM E831

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, xflow	2.93E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	1.21E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	2.93E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	300	°C	ISO 75/Af
PHYSICAL [1]			
Density	1.413	g/cm³	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.08	%	ASTM D570
Mold Shrinkage, flow, 24 hrs [2]	0.1	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs [2]	0.4	%	ASTM D955
Mold Shrinkage, flow, 24 hrs [2]	0.12	%	ISO 294
Mold Shrinkage, xflow, 24 hrs [2]	0.4	%	ISO 294
Wear Factor Washer	55	10^-10 in^5-min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.3	-	ASTM D3702 Modified: Manual
Static COF	0.32	-	ASTM D3702 Modified: Manual
Density	1.4	g/cm³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
FLAME CHARACTERISTICS [3]			
UL Yellow Card Link	E121562-101284441	-	-
UL Recognized, 94V-0 Flame Class Rating	0.77	mm	UL 94
INJECTION MOLDING [4]			
Drying Temperature	150	°C	
Drying Time	4 – 6	Hrs	
Front - Zone 3 Temperature	380 – 400	°C	
Middle - Zone 2 Temperature	380 – 400	°C	
Rear - Zone 1 Temperature	370 – 380	°C	
Mold Temperature	175 – 190	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved