

LNPTM VERTON™ COMPOUND PX91200

PDX-P-91200

DESCRIPTION

LNP VERTON PX91200 is a compound based on Polyamide 6 (Nylon 6) resin containing 35% long glass fiber and proprietary lubricants. Added features include High Impact, Structural and Wear resistant.

GENERAL INFORMATION	
Features	Wear resistant, High stiffness/Strength
Fillers	Glass Fiber, Proprietary Filler
Polymer Types	Polyamide 6 (Nylon 6)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Exteriors
Building and Construction	Building Component
Consumer	Sport/Leisure, Home Appliances, Commercial Appliance
Industrial	Industrial General

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	181	MPa	ISO 527
Tensile Strain, break	2	%	ISO 527
Tensile Modulus, 1 mm/min	12100	MPa	ISO 527
Flexural Stress	250	MPa	ISO 178
Flexural Modulus	10290	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched 80*10*4 +23°C	68	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	225	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	222	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Density	1.49	g/cm ³	ISO 1183
INJECTION MOLDING ⁽²⁾			
Drying Temperature	80	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	265 – 275	°C	
Front - Zone 3 Temperature	275 – 290	°C	
Middle - Zone 2 Temperature	265 – 275	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	250 – 260	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.