

# NORYL™ RESIN BN9003G

REGION EUROPE

## DESCRIPTION

NORYL BN0039 resin is a non-reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This blow moldable grade exhibits a good balance of impact resistance and surface aesthetics. NORYL BN0039 resin, with its Low warpage and dimensional stability, is an excellent candidate for automotive exterior components including spoilers.

| GENERAL INFORMATION   |   |
|-----------------------|---|
| Features              | Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability |
| Fillers               | Unreinforced  |
| Polymer Types         | Polyphenylene Ether + PS (PPE+PS)   |
| Processing Techniques | Extrusion Blow Molding  |

| INDUSTRY   | SUB INDUSTRY         |
|------------|----------------------|
| Automotive | Automotive Exteriors |

## TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES                                   | TYPICAL VALUES | UNITS             | TEST METHODS |
|--|----------------|-------------------|--------------|
| <b>MECHANICAL <sup>(1)</sup></b>             |                |                   |              |
| Tensile Stress, yld, Type I, 50 mm/min       | 48             | MPa               | ASTM D638    |
| Tensile Stress, brk, Type I, 50 mm/min       | 42             | MPa               | ASTM D638    |
| Tensile Strain, yld, Type I, 50 mm/min       | 3.6            | %                 | ASTM D638    |
| Tensile Strain, brk, Type I, 50 mm/min       | 45             | %                 | ASTM D638    |
| Tensile Modulus, 5 mm/min                    | 2240           | MPa               | ASTM D638    |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 70             | MPa               | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 2150           | MPa               | ASTM D790    |
| Tensile Stress, yield, 50 mm/min             | 47             | MPa               | ISO 527      |
| Tensile Stress, break, 50 mm/min             | 42             | MPa               | ISO 527      |
| Tensile Strain, yield, 50 mm/min             | 3.4            | %                 | ISO 527      |
| Tensile Strain, break, 50 mm/min             | 30.4           | %                 | ISO 527      |
| Tensile Modulus, 1 mm/min                    | 2170           | MPa               | ISO 527      |
| Flexural Stress, yield, 2 mm/min             | 75             | MPa               | ISO 178      |
| Flexural Modulus, 2 mm/min                   | 2190           | MPa               | ISO 178      |
| <b>IMPACT <sup>(1)</sup></b>                 |                |                   |              |
| Izod Impact, unnotched, 23°C                 | NB             | J/m               | ASTM D4812   |
| Izod Impact, notched, 23°C                   | 320            | J/m               | ASTM D256    |
| Izod Impact, notched, -30°C                  | 127            | J/m               | ASTM D256    |
| Instrumented Dart Impact Total Energy, 23°C  | 40             | J                 | ASTM D3763   |
| Izod Impact, unnotched 80*10*4 +23°C         | NB             | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, unnotched 80*10*4 -30°C         | 54             | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, notched 80*10*4 +23°C           | 25             | kJ/m <sup>2</sup> | ISO 180/1A   |

| PROPERTIES   | TYPICAL VALUES | UNITS                   | TEST METHODS   |
|--|----------------|-------------------------|----------------|
| Izod Impact, notched 80*10*4 -30°C                 | 10             | kJ/m <sup>2</sup>       | ISO 180/1A     |
| Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm         | 26             | kJ/m <sup>2</sup>       | ISO 179/1eA    |
| Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm        | 12             | kJ/m <sup>2</sup>       | ISO 179/1eA    |
| Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm         | NB             | kJ/m <sup>2</sup>       | ISO 179/1eU    |
| Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm        | 107            | kJ/m <sup>2</sup>       | ISO 179/1eU    |
| <b>THERMAL <sup>(1)</sup></b>                      |                |                         |                |
| Vicat Softening Temp, Rate B/50                    | 141            | °C                      | ASTM D1525     |
| HDT, 0.45 MPa, 3.2 mm, unannealed                  | 124            | °C                      | ASTM D648      |
| HDT, 1.82 MPa, 3.2mm, unannealed                   | 108            | °C                      | ASTM D648      |
| CTE, -40°C to 40°C, flow                           | 8.6E-05        | 1/°C                    | ASTM E831      |
| CTE, -40°C to 40°C, xflow                          | 9.5E-05        | 1/°C                    | ASTM E831      |
| CTE, -40°C to 40°C, flow                           | 8.6E-05        | 1/°C                    | ISO 11359-2    |
| CTE, -40°C to 40°C, xflow                          | 9.5E-05        | 1/°C                    | ISO 11359-2    |
| Ball Pressure Test, 75°C +/- 2°C                   | N/A            | -                       | IEC 60695-10-2 |
| Vicat Softening Temp, Rate B/50                    | 127            | °C                      | ISO 306        |
| Vicat Softening Temp, Rate B/120                   | 130            | °C                      | ISO 306        |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm             | 126            | °C                      | ISO 75/Bf      |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm              | 110            | °C                      | ISO 75/Af      |
| <b>PHYSICAL <sup>(1)</sup></b>                     |                |                         |                |
| Specific Gravity                                   | 1.06           | -                       | ASTM D792      |
| Mold Shrinkage on Tensile Bar, flow <sup>(2)</sup> | 0.55 – 0.75    | %                       | SABIC method   |
| Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>        | 0.55 – 0.75    | %                       | SABIC method   |
| Mold Shrinkage, xflow, 3.2 mm <sup>(2)</sup>       | 0.55 – 0.75    | %                       | SABIC method   |
| Melt Flow Rate, 280°C/5.0 kgf                      | 10             | g/10 min                | ASTM D1238     |
| Density  | 1.06           | g/cm <sup>3</sup>       | ISO 1183       |
| Water Absorption, (23°C/saturated)                 | 0.25           | %                       | ISO 62-1       |
| Moisture Absorption (23°C / 50% RH)                | 0.05           | %                       | ISO 62         |
| Melt Volume Rate, MVR at 280°C/5.0 kg              | 12             | cm <sup>3</sup> /10 min | ISO 1133       |
| <b>EXTRUSION BLOW MOLDING</b>                      |                |                         |                |
| Drying Temperature                                 | 80 – 85        | °C                      |                |
| Drying Time  | 2 – 4          | Hrs                     |                |
| Melt Temperature (Parison)                         | 235 – 260      | °C                      |                |
| Barrel - Zone 1 Temperature                        | 225 – 260      | °C                      |                |
| Barrel - Zone 2 Temperature                        | 230 – 260      | °C                      |                |
| Barrel - Zone 3 Temperature                        | 235 – 260      | °C                      |                |
| Barrel - Zone 4 Temperature                        | 235 – 260      | °C                      |                |
| Adapter - Zone 5 Temperature                       | 235 – 260      | °C                      |                |
| Head - Zone 6 - Top Temperature                    | 235 – 260      | °C                      |                |
| Head - Zone 7 - Middle Temperature                 | 235 – 260      | °C                      |                |
| Head - Zone 7 - Bottom Temperature                 | 235 – 260      | °C                      |                |
| Mold Temperature                                   | 65 – 95        | °C                      |                |
| Die Temperature                                    | 235 – 260      | °C                      |                |

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.