

# LNPTM COLORCOMPTM COMPOUND GX02708H

PDX-G-02708 HC

## DESCRIPTION

LNP COLORCOMP GX02708H compound is based on Polysulfone (PSU) resin. Added features of this grade include: Healthcare.

GENERAL INFORMATION	
Features	Aesthetics/Visual effects, Healthcare/Formula lock, High temperature resistance, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polysulfone (PSU)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Hygiene and Healthcare	Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing
Packaging	Industrial Packaging

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL <sup>(1)</sup>			
HDT, 1.82 MPa, 3.2mm, unannealed	174	°C	ASTM D648
CTE, -30°C to 30°C, flow	5.6E-05	1/°C	ASTM D696
PHYSICAL <sup>(1)</sup>			
Specific Gravity	1.24	-	ASTM D792
Moisture Absorption, (23°C/50% RH/24 hrs)	0.3	%	ASTM D570
ELECTRICAL <sup>(1)</sup>			
Dielectric Strength, 1.6 mm	130	kV/mm	ASTM D149
Dissipation Factor, 1 MHz	0.006	-	ASTM D150
FLAME CHARACTERISTICS			
Oxygen Index (LOI)	26	%	ASTM D2863
INJECTION MOLDING <sup>(2)</sup>			
Drying Temperature	120 – 150	°C	
Drying Time	4	Hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	360 – 370	°C	
Front - Zone 3 Temperature	350 – 360	°C	
Middle - Zone 2 Temperature	340 – 350	°C	
Rear - Zone 1 Temperature	325 – 340	°C	
Mold Temperature	150	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.