

# NORYL™ RESIN SE1X

REGION AMERICAS

## DESCRIPTION

NORYL SE1X resin is a non-reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This injection moldable grade contains non-brominated, non-chlorinated flame retardant and carries a UL94 flame rating of V0/V1 at 1.5mm along with a UL746C Outdoor Suitability rating of F1. NORYL SE1X resin offers strong electrical performance, low moisture absorption, dimensional stability, and hydrolytic stability. This material is an excellent candidate for indoor and outdoor electrical enclosures, heating ventilation / air conditioning (HVAC) applications, and solar / photovoltaic (PV) junction box applications. \*for enhanced processing version, please see NORYL NH5120 resin grade.

GENERAL INFORMATION	
Features	Flame Retardant, Low Warpage, Amorphous, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PS (PPE+PS)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Home Appliances, Commercial Appliance
Electrical and Electronics	Electronic Components, Mobile Phone - Computer - Tablets
Industrial	Electrical

## TYPICAL PROPERTY VALUES

Revision 20250122

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	53	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	15	%	ASTM D638
Tensile Modulus, 50 mm/min	2500	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	100	MPa	ASTM D790
Flexural Stress, yld, 2.6 mm/min, 100 mm span	100	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2700	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	2400	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	61	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.3	%	ISO 527
Tensile Strain, break, 50 mm/min	20.7	%	ISO 527
Tensile Modulus, 1 mm/min	2670	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	99	MPa	ISO 178
Flexural Modulus, 2 mm/min	2560	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, unnotched, 23°C	2600	J/m	ASTM D4812
Izod Impact, notched, 23°C	180	J/m	ASTM D256
Izod Impact, notched, -30°C	106	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	49	J	ASTM D3763
Izod Impact, notched 80°10°4 +23°C	14	kJ/m <sup>2</sup>	ISO 180/1A
<b>THERMAL <sup>(1)</sup></b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	126	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	112	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	126	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	118	°C	ASTM D648
CTE, -40°C to 40°C, flow	8.04E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	8.81E-05	1/°C	ASTM E831
Vicat Softening Temp, Rate B/50	132	°C	ISO 306
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120°10°4 sp=100mm	129	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120°10°4 sp=100mm	115	°C	ISO 75/Ae
Relative Temp Index, Elec <sup>(2)</sup>	110	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	105	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	110	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.1	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.06	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm <sup>(3)</sup>	0.5 – 0.7	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow <sup>(3)</sup>	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	8.5	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 280°C/5.0 kg	8	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity	2.3E+16	Ω.cm	ASTM D257
Surface Resistivity	>1.E+15	Ω	ASTM D257
Dielectric Strength, in oil, 3.2 mm	18.1	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	2.52	-	ASTM D150
Relative Permittivity, 1 MHz	2.46	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0034	-	ASTM D150
Dissipation Factor, 1 MHz	0.0021	-	ASTM D150
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 0	≥1.5	mm	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D495
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E121562-100107130</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	≥6	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥1.5	mm	UL 94
Glow Wire Flammability Index, 1.0 mm	900	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	900	°C	IEC 60695-2-12

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	700	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	700	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	725	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	725	°C	IEC 60695-2-13
Radiant Panel Listing	RP100	-	UL Tested
UV-light, water exposure/immersion	F1	-	UL 746C
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 3	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	280 – 310	°C	
Nozzle Temperature	280 – 310	°C	
Front - Zone 3 Temperature	270 – 310	°C	
Middle - Zone 2 Temperature	260 – 305	°C	
Rear - Zone 1 Temperature	250 – 300	°C	
Mold Temperature	75 – 105	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses, colors and regions. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.