

LNPT[™] THERMOTUF[™] COMPOUND VC006

VC-1006

REGION ASIA

DESCRIPTION

LNP THERMOTUF VC006 compound is based on Super Tough Nylon resin containing 30% carbon fiber. Added features of this grade include: Impact Modified, Electrically Conductive.

GENERAL INFORMATION	
Features	Electrically Conductive, Carbon fiber filled, High stiffness/Strength, Impact resistant
Fillers	Carbon Fiber
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical, Defense

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	157	MPa	ASTM D638
Tensile Strain, break	2.4	%	ASTM D638
Tensile Modulus, 50 mm/min	16370	MPa	ASTM D638
Flexural Stress	241	MPa	ASTM D790
Flexural modulus	14550	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	843	J/m	ASTM D4812
Izod Impact, notched, 23°C	149	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	250	°C	ASTM D648
PHYSICAL ⁽¹⁾			
Density	1.22	g/cm ³	ASTM D792

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.