

# LNPT<sup>TM</sup> THERMOCOMP<sup>TM</sup> COMPOUND WX15004L

## DESCRIPTION

LNP THERMOCOMP WX15004L is a compound based on Polybutylene Terephthalate + PET (PBT+PET) resin, containing 30% glass fiber. Added features of this material include: Mold Release, Heat Stabilizer. Material is suitable for food contact applications.

GENERAL INFORMATION	
Features	Heat Stabilized, Food contact, Enhanced mold release, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber
Polymer Types	Polybutylene Terephthalate + PET (PBT+PET)
Processing Techniques	Injection Molding

  

INDUSTRY	SUB INDUSTRY
Consumer	Consumer Goods, Home Appliances
Industrial	Industrial General

## TYPICAL PROPERTY VALUES

Revision 20231123

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yield, 5 mm/min	140	MPa	ISO 527
Tensile Stress, break, 5 mm/min	140	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.5	%	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	9000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	200	MPa	ISO 178
Flexural Modulus, 2 mm/min	8000	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	9	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL <sup>(1)</sup></b>			
CTE, 23°C to 80°C, flow	2.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.1E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	200	°C	ISO 306
Vicat Softening Temp, Rate B/120	205	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	202	°C	ISO 75/Ae
<b>PHYSICAL <sup>(1)</sup></b>			
Moisture absorption (23°C/50% RH)	0.06	%	-
Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>	0.3 – 0.8	%	SABIC method
Density	1.54	g/cm <sup>3</sup>	ISO 1183

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, (23°C/saturated)	0.15	%	ISO 62-1
Melt Volume Rate, MVR at 260°C/2.16 kg	13	cm <sup>3</sup> /10 min	ISO 1133
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	110 – 120	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 285	°C	
Nozzle Temperature	265 – 275	°C	
Front - Zone 3 Temperature	260 – 280	°C	
Middle - Zone 2 Temperature	255 – 280	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	60 – 110	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.