ULTEM™ RESIN SF2260

REGION ASIA

DESCRIPTION

20% Glass fiber filled, super high flow for thin wall application.

TYPICAL PROPERTY VALUES

Revision 20260326

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	148	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2.4	%	ASTM D638
Tensile Modulus, 5 mm/min	9400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	191	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	7360	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	142	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.4	%	ISO 527
Flexural Modulus, 2 mm/min	7170	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	80	J/m	ASTM D256
Izod Impact, notched 80*10*4 +23°C	8	kJ/m²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	201	°C	ASTM D648
CTE, -40°C to 150°C, flow	1.4E-05	1/°C	ASTM E831
CTE, -40°C to 150°C, xflow	5.4E-05	1/°C	ASTM E831
CTE, 23°C to 150°C, flow	1.8E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	6.7E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec [1]	105	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	105	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	105	°C	UL 746B
PHYSICAL			
Specific Gravity	1.42	-	ASTM D792
Moisture absorption (23°C/50% RH)	0.05	%	-
Mold Shrinkage, flow	0.46	%	SABIC method
Mold Shrinkage, xflow	0.54	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	30	g/10 min	ASTM D1238
Density	1.42	g/cm³	ISO 1183
Water Absorption, (23°C/24hrs)	0.14	%	ISO 62-1
Melt Volume Rate			
345°C/10.0 kg	70	cm³/10 min	ISO 1133
FLAME CHARACTERISTICS [1]			
UL Yellow Card Link	E45587-101275405	-	-
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	150	°C	

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved