

LEXAN™ COPOLYMER CFR9712

REGION EUROPE

DESCRIPTION

LEXAN CFR9712 Polycarbonate (PC) resin is a non-filled, injection moldable grade. This non-chlorinated, non-brominated flame retardant PC has an UL-94 V0 rating at 2.0 mm and high flow capability. LEXAN CFR9712 is available in clear transparent and tinted color options that is an excellent candidate for a wide variety of applications.

TYPICAL PROPERTY VALUES

Revision 20230720

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	66	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	51	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	55	%	ASTM D638
Tensile Modulus, 50 mm/min	2450	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	105	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2370	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	56	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	78	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	97	MPa	ISO 178
Flexural Modulus, 2 mm/min	2400	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	NB	J/m	ASTM D4812
Izod Impact, notched, 23°C	100	J/m	ASTM D256
Izod Impact, notched, -30°C	90	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	60	J	ASTM D3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	10	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	30	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	10	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate B/50	136	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	130	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.8E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ASTM E831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, 23°C to 80°C, flow	7.8E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.6E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	Pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	130	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	120	°C	ISO 75/Ae
Relative Temp Index, Elec ⁽²⁾	130	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	120	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	130	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.19	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.55 – 0.75	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽³⁾	0.6 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	30	g/10 min	ASTM D1238
Density	1.2	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.14	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.11	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	29	cm ³ /10 min	ISO 1133
OPTICAL ⁽¹⁾			
Light Transmission at 1.0 mm	>90	%	SABIC method
Light Transmission at 2.0 mm	>89	%	SABIC method
Light Transmission at 3.0 mm	>88	%	SABIC method
ELECTRICAL ⁽¹⁾			
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥1.7	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥0.4	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 1	≥2	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 2	≥0.4	mm	UL 746A
Dielectric Constant (Dk), 1.1 GHz	2.78	-	ASTM ES 7-83
Dissipation Factor (Df), 1.1 GHz	0.0056	-	ASTM ES 7-83
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E45329-100919721	-	-
UL Recognized, 94V-0 Flame Class Rating	≥2	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥1.7	mm	UL 94
UL Recognized, 94V-2 Flame Class Rating	≥0.4	mm	UL 94
Glow Wire Ignitability Temperature, 3.0 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.7 mm	850	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.7 mm	960	°C	IEC 60695-2-12
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	280 – 305	°C	
Nozzle Temperature	275 – 300	°C	
Front - Zone 3 Temperature	280 – 305	°C	
Middle - Zone 2 Temperature	270 – 295	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.