

LNPT[™] ELCRIN[™] EXL9353RCC

DESCRIPTION

ELCRIN EXL9353RCC polycarbonate (PC) siloxane copolymer resin is a UV stabilized, medium flow, non-chlorinated, non-brominated flame retardant opaque grade with 50% post consumer recycle (PCR) content. This resin offers excellent low temperature ductility (-30 °C), UL94 V0 at 1.5mm, good chemical resistance and in combination with excellent processability and release with opportunities for shorter cycle times compared to standard PC. ELCRIN EXL9353RCC resin is a product available in wide range of opaque colors and excellent candidate for a wide variety of applications.

GENERAL INFORMATION	
Features	Flame Retardant, Chemical Resistance, Good Processability, Sustainable (Mechanical Recycling), Non Cl/Br flame retardant, Low temperature impact
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Consumer	Personal Accessory, Home Appliances
Electrical and Electronics	Electrical Devices and Displays, Electrical Components and Infrastructure

TYPICAL PROPERTY VALUES

Revision 20240823

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	61	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Modulus, 50 mm/min	2130	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	88	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2200	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	57	MPa	ISO 527
Tensile Stress, break, 50 mm/min	54	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.5	%	ISO 527
Tensile Strain, break, 50 mm/min	90	%	ISO 527
Tensile Modulus, 1 mm/min	2140	MPa	ISO 527
Flexural Strength, 2 mm/min	88	MPa	ISO 178
Flexural Modulus, 2 mm/min	2220	MPa	ISO 178
Hardness, Rockwell L	87	-	ASTM D785
Hardness, Rockwell R	119	-	ASTM D785
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	920	J/m	ASTM D256
Izod Impact, notched, 0°C	830	J/m	ASTM D256
Izod Impact, notched, -30°C	630	J/m	ASTM D256
Izod Impact, notched, -40°C	300	J/m	ASTM D256

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*3 +23°C	73	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	45	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	76	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	47	kJ/m ²	ISO 179/1eA
Instrumented Dart Impact Total Energy, 23°C	67	J	ASTM D3763
Instrumented Dart Impact Total Energy, -30°C	67	J	ASTM D3763
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	128	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	116	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	129	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	116	°C	ISO 75/Af
CTE, -40°C to 40°C, flow	7.1E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.4E-05	1/°C	ASTM E831
CTE, 23°C to 80°C, flow	7.9E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.1E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	135	°C	ISO 306
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
PHYSICAL ⁽¹⁾			
Specific Gravity	1.19	-	ASTM D792
Density	1.19	g/cm ³	ISO 1183
Melt Flow Rate, 300°C/1.2 kgf	11	g/10 min	ASTM D1238
Melt Volume Rate, MVR at 300°C/1.2 kg	10	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽²⁾	0.4 – 0.8	%	SABIC method
ELECTRICAL ⁽¹⁾			
Surface Resistivity	>1E+16	Ω	ASTM D257
Volume Resistivity	>1E+16	Ω.cm	ASTM D257
Dielectric Constant, 1.1 GHz	2.93	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0066	-	SABIC method
Dielectric Constant, 1.9 GHz	2.91	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0061	-	SABIC method
Dielectric Constant, 5 GHz	2.85	-	SABIC method
Dissipation Factor, 5 GHz	0.0057	-	SABIC method
Dielectric Constant, 10 GHz	2.88	-	SABIC method
Dissipation Factor, 10 GHz	0.006	-	SABIC method
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link ⁽³⁾	E207780-104590743	-	-
UL Recognized, 94V-0 Flame Class Rating ⁽³⁾	≥1.5	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating ⁽³⁾	≥3	mm	UL 94
Oxygen Index (LOI)	39	%	ISO 4589
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	875	°C	IEC 60695-2-13
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	120	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	275 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.