

LNPTM ELCRINTM EXL8423RCC

DESCRIPTION

LNP ELCRIN EXL8423RCC is based on Polycarbonate (PC) siloxane copolymer resin. Added features of this grade include: Medium Flow, Colorable, Low Temperature Ductility and 20% Post Consumer Recycle (PCR) content. This grade is targeted for applications that require improved aesthetics and wider color space to overcome restricted color space of traditional PCR grades.

GENERAL INFORMATION	
Features	Sustainable (Mechanical Recycling), Aesthetics/Visual effects, Impact resistant, Low temperature impact, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Recreational/Specialty Vehicles
Building and Construction	Building Component
Consumer	Personal Accessory, Home Appliances
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yield, 50 mm/min	57	MPa	ISO 527
Tensile Stress, break, 50 mm/min	65	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	135	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Modulus, 2 mm/min	2170	MPa	ISO 178
Flexural Strength, 2 mm/min	88	MPa	ISO 178
Tensile Modulus, 50 mm/min	2100	MPa	ASTM D638
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	60	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	117	%	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	94	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2200	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, notched 80*10*4 +23°C	69	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	230	kJ/m ²	ISO 180/1U
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	307	kJ/m ²	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	74	kJ/m ²	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched, 23°C	930	J/m	ASTM D256
Izod Impact, unnotched, 23°C	2540	J/m	ASTM D4812
THERMAL ⁽¹⁾			
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	126	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Bf
Vicat Softening Temp, Rate B/50	144	°C	ISO 306
Vicat Softening Temp, Rate B/120	145	°C	ISO 306
CTE, 23°C to 80°C, flow	6.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	6.4E-05	1/°C	ISO 11359-2
HDT, 1.82 MPa, 3.2mm, unannealed	127	°C	ASTM D648
HDT, 0.45 MPa, 3.2 mm, unannealed	141	°C	ASTM D648
Vicat Softening Temp, Rate B/50	145	°C	ASTM D1525
Vicat Softening Temp, Rate B/120	145	°C	ASTM D1525
CTE, 23°C to 50°C, flow	6.5E-05	1/°C	ASTM E831
CTE, 23°C to 50°C, xflow	6.4E-05	1/°C	ASTM E831
Relative Temp Index, Elec ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	80	°C	UL 746B
PHYSICAL ⁽¹⁾			
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/24hrs)	0.15	%	ISO 62-1
Mold Shrinkage, flow ⁽³⁾	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow ⁽³⁾	0.4 – 0.8	%	SABIC method
Melt Volume Rate, MVR at 300°C/1.2 kg	11	cm ³ /10 min	ISO 1133
Specific Gravity	1.19	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.15	%	ASTM D570
Melt Flow Rate, 300°C/1.2 kgf	12	g/10 min	ASTM D1238
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E207780-104400893	-	-
UL Recognized, 94HB Flame Class Rating	≥0.47	mm	UL 94
INJECTION MOLDING ⁽⁴⁾			
Drying Temperature	120	°C	
Drying Time (Cumulative)	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Nozzle Temperature	295 – 315	°C	
Melt Temperature	270 – 295	°C	
Front - Zone 3 Temperature	280 – 305	°C	
Middle - Zone 2 Temperature	295 – 315	°C	
Rear - Zone 1 Temperature	290 – 310	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.