

# LEXANT™ VISUALFX™ RESIN FXE1414L

REGION EUROPE

## DESCRIPTION

Opaque EXL, UV-Stabilized & light shielding capability (Wall thickness >0.8mm), for portable electronics device enclosure application. Only available in white, grey and limited pastel colors. Consult CIC or PM for color availability & limitation.

## TYPICAL PROPERTY VALUES

Revision 20231109

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 50 mm/min	52	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	54	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	84	%	ASTM D638
Tensile Modulus, 50 mm/min	2030	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	86	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2050	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	52	MPa	ISO 527
Tensile Stress, break, 50 mm/min	47	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	75	%	ISO 527
Tensile Modulus, 1 mm/min	2000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	83	MPa	ISO 178
Flexural Modulus, 2 mm/min	2110	MPa	ISO 178
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	766	J/m	ASTM D256
Izod Impact, notched, -30°C	640	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	68	J	ASTM D3763
<b>THERMAL <sup>(1)</sup></b>			
Vicat Softening Temp, Rate B/50	138	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	121	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.73E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, flow	7.02E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.23E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	146	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	118	°C	ISO 75/Af
Relative Temp Index, Elec <sup>(2)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(2)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(2)</sup>	80	°C	UL 746B
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.28	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm <sup>(3)</sup>	0.4 – 0.8	%	SABIC method

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Flow Rate, 300°C/ 1.2 kgf	11	g/ 10 min	ASTM D1238
Density	1.28	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.17	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 300°C/ 1.2 kg	10	cm <sup>3</sup> / 10 min	ISO 1133
<b>FLAME CHARACTERISTICS <sup>(2)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-642296</a>	-	-
UL Recognized, 94HB Flame Class Rating	0.4	mm	UL 94
<b>INJECTION MOLDING <sup>(4)</sup></b>			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	70 – 95	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.