

LNPTM STAT-LOYTM COMPOUND D3000I

DESCRIPTION

LNP STAT-LOY D3000I compound is a Polycarbonate (PC) resin based electrically conductive material with colorability, low surface resistivity, high HDT, low temperature impact toughness and good surface quality. This material is targeted for explosive proof application.

GENERAL INFORMATION	
Features	Antistatic, Impact resistant, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polycarbonate (PC)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components

TYPICAL PROPERTY VALUES

Revision 20240716

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, brk, Type I, 50 mm/min	46.7	MPa	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	83.59	%	ASTM D638
Tensile Modulus, 50 mm/min	1888	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	70.1	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1730	MPa	ASTM D790
Tensile Stress, break, 50 mm/min	44.2	MPa	ISO 527
Tensile Strain, break, 50 mm/min	81.28	%	ISO 527
Tensile Modulus, 1 mm/min	1873	MPa	ISO 527
Flexural Strength, 2 mm/min	71.2	MPa	ISO 178
Flexural Modulus, 2 mm/min	1862	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact			
notched, 23°C	669	J/m	ASTM D256
unnotched, 23°C	NB	J/m	ASTM D4812
notched, -30°C	505	J/m	ASTM D256
unnotched, -30°C	NB	J/m	ASTM D4812
notched, -40°C	237	J/m	ASTM D256
unnotched, -40°C	NB	J/m	ASTM D4812
Izod Impact, notched 80*10*4 +23°C	65.21	kJ/m ²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	60.58	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL ⁽¹⁾			
HDT, 0.45 MPa, 3.2 mm, unannealed	121	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	105	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	124	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	115	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	121	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	100	°C	ISO 75/Af
CTE			
-40°C to 80°C, flow	8.1E-5	1/°C	ASTM E831
-40°C to 80°C, xflow	9.9E-5	1/°C	ASTM E831
-40°C to 80°C, flow	7.8E-5	1/°C	ISO 11359-2
-40°C to 80°C, xflow	1.0E-4	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B / 120	121	°C	ASTM D1525
Vicat Softening Temp, Rate B / 120	120	°C	ISO 306
PHYSICAL ⁽¹⁾			
Specific Gravity	1.18	-	ASTM D792
Melt Flow Rate, 260°C / 1.2 kgf	13.7	g / 10 min	ASTM D1238
Moisture Absorption (23°C / 50% RH)	0.14	%	ISO 62
Mold Shrinkage, flow ⁽²⁾	0.73	%	SABIC method
Mold Shrinkage, xflow ⁽²⁾	0.93	%	SABIC method
ELECTRICAL ⁽¹⁾			
Surface Resistivity	4.4E+10	Ω	ASTM D257
Volume Resistivity	1.3E+11	Ω.cm	ASTM D257
Surface Resistivity	5.0E+9	Ω	ANSI/ESD STM11.13
Dielectric Constant, 1.1 GHz	3.02	-	SABIC method
Dissipation Factor, 1.1 GHz	0.03358	-	SABIC method
Dielectric Constant, 1.9 GHz	2.96	-	SABIC method
Dissipation Factor, 1.9 GHz	0.03144	-	SABIC method
Dielectric Constant, 5 GHz	2.93	-	SABIC method
Dissipation Factor, 5 GHz	0.02694	-	SABIC method
Dielectric Constant, 10 GHz	2.95	-	SABIC method
Dissipation Factor, 10 GHz	0.02242	-	SABIC method
Dielectric Constant, 20 GHz	2.77	-	SABIC method
Dissipation Factor, 20 GHz	0.02251	-	SABIC method
INJECTION MOLDING ⁽³⁾			
Drying Temperature	75 – 80	°C	
Drying Time	6 – 8	Hrs	
Melt Temperature	240 – 260	°C	
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	240 – 260	°C	
Middle - Zone 2 Temperature	240 – 260	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Mold Temperature	40 – 60	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.