

LNPTM STAT-KONTM COMPOUND RD0001

R-HI
REGION ASIA

DESCRIPTION

LNP STAT-KON RD0001 compound is based on Nylon 6/6 resin containing conductive carbon powder. Added features of this grade include: Electrically Conductive, High Impact.

GENERAL INFORMATION	
Features	Electrically Conductive, Impact resistant, No PFAS intentionally added
Fillers	Carbon Powder
Polymer Types	Polyamide 66 (Nylon 66)
Processing Techniques	Injection Molding
INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Electronic Components
Industrial	Material Handling

TYPICAL PROPERTY VALUES

Revision 20241028

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, break	46	MPa	ASTM D638
Tensile Strain, break	13.5	%	ASTM D638
Tensile Modulus, 50 mm/min	2120	MPa	ASTM D638
Flexural Stress	82	MPa	ASTM D790
Flexural Modulus	2620	MPa	ASTM D790
IMPACT ⁽¹⁾			
Izod Impact, unnotched, 23°C	1810	J/m	ASTM D4812
Izod Impact, notched, 23°C	150	J/m	ASTM D256
THERMAL ⁽¹⁾			
HDT, 1.82 MPa, 3.2mm, unannealed	73	°C	ASTM D648
CTE, -40°C to 40°C, flow	1.21E-04	1/°C	ASTM E831
Thermal Conductivity	2.8	W/m·°C	ASTM E1530
PHYSICAL ⁽¹⁾			
Density	1.15	g/cm ³	ASTM D792
ELECTRICAL ⁽¹⁾			
Surface Resistivity ⁽²⁾	1.E+01 – 1.E+06	Ω	ASTM D257

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurement meets requirements as specified in ASTM D4496.



ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.