

VALOX™ FR RESIN ENH4560

REGION EUROPE

DESCRIPTION

VALOX ENH4560 is a 30% glass fiber reinforced, non-chlorinated/brominated flame retardant Polybutylene Terephthalate (PBT) injection moldable grade with excellent chemical resistance. It has a UL94V0@0.80mm, 5VA/5VB@1.5mm flame rating. This is a good candidate for a variety of applications needing a sustainable FR PBT solution.

TYPICAL PROPERTY VALUES

Revision 20241017

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	105	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	105	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	2	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D638
Tensile Modulus, 5 mm/min	11000	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	160	MPa	ASTM D790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	160	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	9300	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	108	MPa	ISO 527
Tensile Stress, break, 5 mm/min	108	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	11000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	175	MPa	ISO 178
Flexural Stress, break, 2 mm/min	175	MPa	ISO 178
Flexural Strain, break, 2 mm/min	2	%	ISO 178
Flexural Modulus, 2 mm/min	10000	MPa	ISO 178
Ball Indentation Hardness, H358/30	142	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
IMPACT ⁽¹⁾			
Charpy Impact, unnotched, 23°C	40	kJ/m ²	ISO 179/2C
Charpy Impact, unnotched, -30°C	35	kJ/m ²	ISO 179/2C
Izod Impact, unnotched, 23°C	570	J/m	ASTM D4812
Izod Impact, unnotched, -30°C	500	J/m	ASTM D4812
Izod Impact, notched, 23°C	72	J/m	ASTM D256
Izod Impact, notched, 0°C	72	J/m	ASTM D256
Izod Impact, notched, -30°C	65	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	37	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	37	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	9	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	8	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	10	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	10	kJ/m ²	ISO 179/2C

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
THERMAL ⁽¹⁾			
Vicat Softening Temp, Rate A/50	217	°C	ASTM D1525
Vicat Softening Temp, Rate B/50	200	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	223	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	205	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	2.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.5E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	220	°C	ISO 306
Vicat Softening Temp, Rate B/50	200	°C	ISO 306
Vicat Softening Temp, Rate B/120	205	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	225	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	205	°C	ISO 75/Af
Relative Temp Index, Elec ⁽²⁾	140	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽²⁾	125	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽²⁾	140	°C	UL 746B
PHYSICAL ⁽¹⁾			
Specific Gravity	1.56	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm ⁽³⁾	0.28	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm ⁽³⁾	0.57	%	SABIC method
Filler Content	30	%	ASTM D229
Melt Flow Rate, 265°C/5.0 kgf	23	g/10 min	ASTM D1238
Density	1.56	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	0.23	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	16	cm ³ /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	110	Pa-s	ISO 11443
ELECTRICAL ⁽¹⁾			
Volume Resistivity	1.0E+14	Ω.cm	ASTM D257
Dielectric Strength, in oil, 0.8 mm	32	kV/mm	ASTM D149
Dielectric Strength, in oil, 1.6 mm	22	kV/mm	ASTM D149
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	ASTM D149
Relative Permittivity, 1 MHz	3.8	-	ASTM D150
Dissipation Factor, 1 MHz	0.14	-	ASTM D150
Volume Resistivity	1.E+14	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 0.8 mm	32	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	22	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.8	-	IEC 60250
Dissipation Factor, 1 MHz	0.14	-	IEC 60250
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index ⁽⁴⁾	600	V	IEC 60112

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Hot-Wire Ignition (HWI), PLC 0	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥0.8	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥0.8	mm	UL 746A
FLAME CHARACTERISTICS ⁽²⁾			
UL Yellow Card Link	E45329-100522223	-	-
UL Yellow Card Link 2	E45329-104546523	-	-
UL Recognized, 94-5VB Flame Class Rating	≥1.5	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	≥1.5	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥0.8	mm	UL 94
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	750	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.0 mm	750	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 0.8 mm	750	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 0.8 mm	960	°C	IEC 60695-2-12
UV-light, water exposure /immersion	F1	-	UL 746C
INJECTION MOLDING ⁽⁵⁾			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	230 – 255	°C	
Front - Zone 3 Temperature	240 – 260	°C	
Middle - Zone 2 Temperature	235 – 250	°C	
Rear - Zone 1 Temperature	230 – 240	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.
- (3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article. The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (4) Value shown here is based on internal measurement.
- (5) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.