LNP™ THERMOCOMP™ Compound OF008E

OF-1008 EM
REGION ASIA

DESCRIPTION

LNP THERMOCOMP OF008E compound is based on linear Polyphenylene Sulfide (PPS) resin containing 40% glass fiber. Added features of this grade include: Easy Molding.

GENERAL INFORMATION	
Features	Good Processability, High stiffness/Strength, No PFAS intentionally added
Fillers	Glass Fiber (Total fluorine >50ppm only from inorganic fluorine)
Polymer Types	Polyphenylene Sulfide, Linear (PPS, Linear)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Consumer	Sport/Leisure, Personal Accessory, Home Appliances, Commercial Appliance
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical

TYPICAL PROPERTY VALUES

Revision 20260204

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, break	178	MPa	ASTM D638
Tensile Strain, break	1.7	%	ASTM D638
Flexural Stress	248	MPa	ASTM D790
Flexural Modulus	14260	MPa	ASTM D790
Tensile Stress, break	160	MPa	ISO 527
Tensile Strain, break	1.2	%	ISO 527
Flexural Stress	190	MPa	ISO 178
Flexural Modulus	13400	MPa	ISO 178
IMPACT [1]			
Izod Impact, unnotched, 23°C	587	J/m	ASTM D4812
Izod Impact, notched, 23°C	101	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	21	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m²	ISO 180/1A
THERMAL [1]			
HDT, 1.82 MPa, 3.2mm, unannealed	261	°C	ASTM D648
CTE, -40°C to 40°C, flow	2.6E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	268	°C	ISO 75/Af
PHYSICAL [1]			
Density	1.68	g/cm³	ASTM D792

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 24 hrs [2]	0.2	%	ASTM D955
Mold Shrinkage, xflow, 24 hrs [2]	0.8	%	ASTM D955
Wear Factor Washer	240	10^-10 in^5-min/ft-lb-hr	ASTM D3702 Modified: Manual
Dynamic COF	0.66	-	ASTM D3702 Modified: Manual
Static COF	0.87	-	ASTM D3702 Modified: Manual
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating [3]	0.45	mm	UL 94 by SABIC-IP

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) UL rating shown here is based on internal measurements.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved