

SILTEM™ Resin HUSTM1600

DESCRIPTION

SILTEM™ HUSTM1600 resin is a flexible polyetherimide(PEI)-siloxane copolymer. The intended use for this material is in medical devices and pharmaceutical applications. The material is biocompatible (ISO 10993) and Healthcare management of change applies. The material is RoHS compliant and offers a halogen free (according VDE 0472) flame retardant solution that also offers low smoke emission and toxicity. It is an amber colored transparent material that can be self-colored and easily processed on conventional processing equipment. The material may be used for extrusion of e.g. wire and cable insulation, tubes, corrugated pipes and profiles as well as flexible injection molded parts.

ISCC+ certified renewable bio-based solutions can be made available for this grade via differentiated color nomenclature.

GENERAL INFORMATION	
Applications	Enclosure/Housing/Cover, Fluid Delivery, Wire & cable, medical, medical connector, medical electrical connector
Features	Flame Retardant, Chemical Resistance, Good Processability, High Flow, Low Smoke and Toxicity, Thin Wall, Dielectrics, Amorphous, Flexible, Low Corrosivity, IR Transparent, Low Moisture Absorption, Low Specific Gravity, Bio-Renewable, Transparent/Translucent, Biocompatibility-ISO 10993, Healthcare/Formula lock, Non Cl/Br flame retardant, Non halogenated flame retardant, Dimensional stability, High temperature resistance, No PFAS intentionally added
Fillers	Unreinforced
Brands	SILTEM™
Polymer Types	Polyetherimide (PEI)
Processing Techniques	Compounding Extrusion, Film Extrusion, Injection Molding, Profile Extrusion, Extrusion, Compression molding, Injection compression molding, Pipe extrusion, Foam Extrusion
INDUSTRY	
Hygiene and Healthcare	General Healthcare

TYPICAL PROPERTY VALUES

Revision 20260907

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	43	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	40	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	10	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	64	%	ASTM D638
Tensile Modulus, 5 mm/min	1400	MPa	ASTM D638
Flexural Stress	48	MPa	ASTM D790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	48	MPa	ASTM D790
Flexural Modulus	1250	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1250	MPa	ASTM D790
Hardness, Shore D	72	-	ASTM D2240
Taber Abrasion, CS-17, 1 kg	50	mg/1000cy	ASTM D1044
Tensile Stress, yield, 50 mm/min	42	MPa	ISO 527
Tensile Stress, break, 50 mm/min	41	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	10	%	ISO 527
Tensile Strain, break, 50 mm/min	74	%	ISO 527

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Tensile Modulus, 1 mm/min	1380	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	55	MPa	ISO 178
Flexural Modulus, 2 mm/min	1250	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	412	J/m	ASTM D256
Izod Impact, notched 80*10*4 +23°C	36	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	25	kJ/m²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	80	°C	ASTM D648
Vicat Softening Temp, Rate B/120	167	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	144	°C	ISO 75/Bf
PHYSICAL			
Specific Gravity	1.19	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.86 – 1.01	%	SABIC method
Melt Flow Rate			
295°C/6.6 kgf	8.6	g/10 min	ASTM D1238
Density	1.19	g/cm³	ISO 1183
Water Absorption, (23°C/24hrs)	0.58	%	ISO 62-1
Water Absorption, (23°C/saturated)	0.58	%	ISO 62-1
Matrix Tg	195	°C	DMA
ELECTRICAL			
Volume Resistivity	1.E+16	Ω.cm	ASTM D257
Surface Resistivity	1.E+15	Ω	ASTM D257
Dielectric Strength, in oil, 3.2 mm	16.6	kV/mm	ASTM D149
Relative Permittivity, 100 Hz	3.14	-	ASTM D150
Relative Permittivity, 100 kHz	3	-	ASTM D150
Relative Permittivity, 1 MHz	3.02	-	ASTM D150
Dissipation Factor			
100 Hz	0.014	-	ASTM D150
100 kHz	0.0064	-	ASTM D150
1 MHz	0.0055	-	ASTM D150
Comparative Tracking Index	175	V	IEC 60112
FLAME CHARACTERISTICS			
UL Compliant, 94V-0 Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
Oxygen Index (LOI)	48	%	ASTM D2863
INJECTION MOLDING			
Drying Temperature	105	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 320	°C	
Nozzle Temperature	310 – 320	°C	
Front - Zone 3 Temperature	310 – 320	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	310 – 320	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	105 – 115	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	
WIRE COATING EXTRUSION			
Drying Temperature	105 – 130	°C	
Drying Time	4 – 6	Hrs	
Maximum Moisture Content	0.02	%	
Compression Ratio	2.1:1 to 2.7:1	-	
Feed - Compression - Metering	10-5-10	D	
Feed Zone Temperature	270 – 310	°C	
Middle Zone Temperatures	280 – 320	°C	
Head Zone Temperature	290 – 330	°C	
Neck Temperature	290 – 330	°C	
Cross-head Temperature	290 – 330	°C	
Die Temperature	290 – 330	°C	
Melt Temperature	290 – 330	°C	
Conductor Pre-heat Temperature	100 – 150	°C	
Screen Pack	100-200mesh	-	
Water Bath Temperature	70 – 90	°C	
Extruder Length/Diameter Ratio (L/D)	22:1 to 28:1	-	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.