

LNPTM THERMOCOMPTM COMPOUND IF004

IF-1004

REGION ASIA

DESCRIPTION

LNP THERMOCOMP IF004 compound is based on Nylon 6/12 resin containing 20% glass fiber.

| GENERAL INFORMATION | |
|-----------------------|------------------------------------------------------|
| Features | High stiffness/Strength, No PFAS intentionally added |
| Fillers | Glass Fiber |
| Polymer Types | Polyamide 612 (Nylon 612) |
| Processing Techniques | Injection Molding |

| INDUSTRY | SUB INDUSTRY |
|----------------------------|--------------------------------------|
| Building and Construction | Building Component, Water Management |
| Consumer | Personal Accessory |
| Electrical and Electronics | Mobile Phone - Computer - Tablets |
| Industrial | Electrical |

TYPICAL PROPERTY VALUES

Revision 20231109

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---------------------------------------------|----------------|-------------------|--------------|
| MECHANICAL ⁽¹⁾ | | | |
| Tensile Stress, break | 123 | MPa | ASTM D638 |
| Tensile Strain, break | 3.6 | % | ASTM D638 |
| Tensile Modulus, 50 mm/min | 5900 | MPa | ASTM D638 |
| Flexural Stress | 186 | MPa | ASTM D790 |
| Flexural modulus | 5660 | MPa | ASTM D790 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, unnotched, 23°C | 823 | J/m | ASTM D4812 |
| Izod Impact, notched, 23°C | 74 | J/m | ASTM D256 |
| THERMAL ⁽¹⁾ | | | |
| HDT, 1.82 MPa, 3.2mm, unannealed | 196 | °C | ASTM D648 |
| PHYSICAL ⁽¹⁾ | | | |
| Density | 1.22 | g/cm ³ | ASTM D792 |
| Mold Shrinkage, flow, 24 hrs ⁽²⁾ | 0.4 | % | ASTM D955 |

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.



ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.