LNP™ THERMOCOMP™ COMPOUND OMC0E

DESCRIPTION

LNP THERMOCOMP OMC0E compound is a mineral reinforced polyphenylene sulfide. Added feature of this material include: high dielectric constant, low dissipation factor, good flame and chemical resistance, low moisture absorption.

GENERAL INFORMATION	
Features	Flame Retardant, Chemical Resistance, Dielectrics, No PFAS intentionally added
Fillers	Mineral
Polymer Types	Polyphenylene Sulfide, Linear (PPS, Linear)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Automotive	Automotive Interiors
Electrical and Electronics	Electronic Components, Wireless Communication

TYPICAL PROPERTY VALUES

Revision 20260805

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, brk, Type I, 5 mm/min	73	MPa	ASTM D638
Tensile Strain, Break			
Type I, 5 mm/min	1.0	%	ASTM D638
5 mm/min	1.0	%	ISO 527
Tensile Modulus, 5 mm/min	10200	MPa	ASTM D638
Flexural Strength, 1.3 mm/min, 50 mm span	103	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	9800	MPa	ASTM D790
Tensile Stress, break, 5 mm/min	74	MPa	ISO 527
Tensile Modulus, 1 mm/min	10300	MPa	ISO 527
Flexural Strength, 2 mm/min	105	MPa	ISO 178
Flexural Modulus, 2 mm/min	10000	MPa	ISO 178
IMPACT [1]			
Izod impact, notched			
23°C	34	J/m	ASTM D256
80*10*4 +23°C	3.6	kJ/m²	ISO 180/1A
80*10*4 0°C	3.5	kJ/m²	ISO 180/1A
80*10*4 -20°C	3.4	kJ/m²	ISO 180/1A
Izod Impact, Unnotched			
23°C	270	J/m	ASTM D4812
80*10*4 +23°C	16	kJ/m²	ISO 180/1U
80*10*4 0°C	16	kJ/m²	ISO 180/1U
80*10*4 -20°C	14	kJ/m²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	3	kJ/m²	ISO 179/1eA

© 2026 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	20	kJ/m²	ISO 179/1eU
THERMAL [1]			
HDT, 0.45 MPa, 3.2 mm, unannealed	220	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	195	°C	ASTM D648
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	220	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	205	°C	ISO 75/Af
CTE			
-40°C to 90°C, flow	4.0E-5	1/°C	ASTM E831
-40°C to 90°C, xflow	4.0E-5	1/°C	ASTM E831
-40°C to 40°C, flow	3.3E-5	1/°C	ISO 11359-2
-40°C to 40°C, xflow	3.3E-5	1/°C	ISO 11359-2
-40°C to 90°C, flow	4.0E-5	1/°C	ISO 11359-2
-40°C to 90°C, xflow	4.0E-5	1/°C	ISO 11359-2
-40°C to 125°C, flow	4.9E-5	1/°C	ISO 11359-2
-40°C to 125°C, xflow	4.9E-5	1/°C	ISO 11359-2
PHYSICAL [1]			
Specific Gravity	2.46	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.02	%	ISO 62-1
Moisture Absorption, (23°C/50% RH/24hrs)	0.01	%	ISO 62-4
Melt Flow Rate			
315°C/5.0 kgf	25	g/10 min	ASTM D1238
Mold Shrinkage, flow [2]	0.7	%	SABIC method
Mold Shrinkage, xflow [2]	0.7	%	SABIC method
ELECTRICAL [1]			
Dielectric Constant			
1.1 GHz	11.1	-	SABIC method
1.9 GHz	11	-	SABIC method
5 GHz	10.85	-	SABIC method
Dissipation Factor			
1.1 GHz	0.0016	-	SABIC method
1.9 GHz	0.0018	-	SABIC method
5 GHz	0.0022	-	SABIC method
INJECTION MOLDING [3]			
Drying Temperature	120 – 140	°C	
Drying Time	3 – 4	Hrs	
Melt Temperature	310 – 330	°C	
Nozzle Temperature	310 – 330	°C	
Front - Zone 3 Temperature	310 – 330	°C	
Middle - Zone 2 Temperature	300 – 320	°C	
Rear - Zone 1 Temperature	290 – 310	°C	
Mold Temperature	135 – 160	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	

© 2026 Copyright by SABIC. All rights reserved

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2026 Copyright by SABIC. All rights reserved